


Features and Components

Ceramic-Coated Roofing Granules: Specifically engineered for optimal embedment in the SBS-blend sheet. The ceramic coating promotes excellent long-term adhesion.

High-Quality SBS Rubber and Asphalt Blend: Provides full recovery properties after 100% elongation and lends elasticity and flexibility to the sheet. Designed for the sharp angle changes and turns found in flashing areas.

Polyester Reinforcement Mat: The 170 g/m² polyester mat provides excellent tensile strength, tear resistance and flexibility.

Self-Adhering Modified Bitumen: The product's self-adhering feature with an easy-to-peel plastic film on the bottom side of the sheet allows for installation without the need of hot asphalt.



System Compatibility

This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	HW	HA	CA	HW	SA	MF	
Compatible with the selected multi-ply systems above									

Single Ply	TPO				PVC			EPDM		
	MF	AD	SA	IW	MF	AD	IW	MF	AD	BA
Do not use in single ply systems										

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%

Peak Advantage® Guarantee Information

Systems	Guarantee Term
When used in most 2-5 ply JM SBS systems.*	Up to 25 years

*Contact JM Technical Services for specific system requirements for guarantee lengths.

Installation/Application



Self-Adhered

- Apply in dry weather and when the roll is at least 60°F (16°C) at the time of application
- Laps may be installed using heat-welding techniques
- Refer to JM SBS modified bitumen specifications and detail drawings for application and slope information

JM Recommended Substrates:

JM CleanBond Cap Flashing may only be applied over JM CleanBond® Base. For recommended substrates, see data sheet for JM CleanBond® Base Flashing (RS-4848).

Packaging and Dimensions

Roll Coverage*	75 ft ² (6.97 m ²)
Roll Length	26' 3" (8 m)
Roll Width	39 3/4" (1 m)
Roll Weight	72 lb (32.7 kg)
Producing Locations	South Gate, CA

*Assumes a 4" side lap.

Tested Physical Properties

Physical Properties		ASTM Test Method	JM CleanBond Cap Flashing	
			MD*	XMD**
Strength	Tensile Tear	D 5147	100 lb/in. (17.5 kN/m)	80 lb/in. (14.0 kN/m)
	Peak Load at 0°F (-18°C)	D 5147	100 lbf/in. W (17.5 kN/m)	80 lbf/in. W (14.0 kN/m)
Longevity	Low Temp. Flexibility (Unconditioned)	D 5147	-10°F (-23°C)	
	Thickness	D 5147	150 mil (3.81 mm)	
	Elongation at Peak Load at 0°F (-18°C)	D 5147	35%	35%
Installation	Dimensional Stability	D 5147	0.7%	0.6%
	Roll Weight	D 146	72 lb (32.7 kg)	

*MD = Machine Direction

**XMD = Cross-Machine Direction

Note: Material tested in accordance with ASTM D 5147 Standard Test Methods for Sampling and Testing Modified Bituminous Sheet Materials.

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The Safety Data Sheet is available by calling (800) 922-5922 or on the web at www.jm.com/roofing. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the regional sales representative nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville roofing products and systems, visit www.jm.com/terms-conditions.