

StarStran® 423 LCF

Product description:

StarStran® LCF fiber glass chopped strands are produced by chopping E glass fibers at specified lengths. StarStran® 423 LCF chopped fibers are coated with a chemical sizing to provide reinforcement of strong lightweight composite panels. Multiple applications can be found in automotive, appliances and other industrial markets.

Benefits:

- Improved productivity
- Excellent dispersion in aqueous media
- Product consistency
- Controlled moisture content
- Supply security
- Formaldehyde free
- Strong lightweight composite panels

Resin compatibility:

- Polypropylene



Designation: Glass Type is E-Glass

JM Designation	Region	Filament diameter (µm)	Sizing designation	Chopped strands length (inch)
StarStran® LCF 1/2" K423	NA	13	423	1/2
StarStran® LCF 1/2" M423	NA	16	423	1/2

Technical Data:

Region	JM Designation	LOI content (%) ISO 1887	Moisture content (%) ISO 3344
NA	StarStran® LCF 1/2" K423	0.12	7
	StarStran® LCF 1/2" M423	0.08	8

Packaging:

Region	Packaging type	Pallet dimensions (inches)	Net weight per pallet (Lb.)	Container per pallet
NA	Bulk Carton	45 X 36	1600	1
	Returnable bin	48.6 X 44.7	2415	1

Storage:

These products should be stored in original packaging in dry, roofed, dust free storehouses. The recommended temperature is between 10°C to 30°C (50°F to 86°F) at relative air humidity between 50% to 75%. The products should remain in the original packaging and be conditioned in the work area for a minimum of 24 hours prior to use. The pallets should be single stacked unless otherwise specified on the packaging unit.

**North America****Warranty disclaimer :**

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of this product represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the Regional Sales Office nearest you for the most current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on Johns Manville products, please visit <https://www.jm.com/en/login/policies-terms-and-conditions/> or call (800)654-3103.

Values:

All data represent typical average values.

**US Headquarters**

Johns Manville
717 17th Street
Denver, CO 80202 - USA
Phone: +1 (303) 978 2000

Customer-Service-Offices:

North America
Johns Manville
7500 Dutch Road
Waterville, OH 43566 - USA
Phone: +1 (800) 554 4826
Fax: +1 (419) 878 1538

Europe

Johns Manville Slovakia, a.s.
Strojárska 1
91799 Tmava - Slovakia
Phone: +421 (0) 33 5918 249
Contact: fibers@jm.com

www.jm.com