



JOHNS MANVILLE
717 17th Street
Denver, Colorado 80202
800-654-3103
www.specjm.com

JM CORBOND® III AND JM CORBOND® IV PERFORMANCE INSULATION SYSTEMS

CSI Section:
07 21 00 Thermal Insulation

1.0 RECOGNITION

Johns Manville JM Corbond® III and JM Corbond® IV Performance Insulation Systems described in this report were evaluated for use as foam plastic insulation. The surface burning characteristics, thermal performance, physical, air infiltration, vapor permeance, fungal resistance, and thermal barrier properties, attic and crawl space installations, and application in Type V construction and in exterior walls of Types I through IV construction were evaluated for compliance with the following codes:

- 2021, 2018, 2015, 2012, and 2009 International Building Code® (IBC)
- 2021, 2018, 2015, 2012, and 2009 International Residential Code® (IRC)
- 2021, 2018, 2015, 2012, and 2009 International Energy Conservation Code® (IECC)
- 2021, 2018, 2015, 2012, and 2009 NFPA 5000 Building Construction and Safety Code™

2.0 LIMITATIONS

Use of the JM Corbond® III and JM Corbond® IV spray-applied foam plastic insulations described in this report is subject to the following limitations:

2.1 The products shall be installed in accordance with the manufacturer's published installation instructions, this evaluation report, and the applicable code. In the event of a conflict, the more restrictive shall govern.

2.2 JM Corbond® III and JM Corbond® IV insulations shall be separated from the interior of the building by a code-complying thermal barrier or ignition barrier as appropriate in accordance with Sections 3.3 and 3.4 of this report.

2.3 The insulation components are produced by Johns Manville under a quality control program with inspections under the supervision of UES.

2.4 JM Corbond® III and JM Corbond® IV insulations shall be installed by contractors certified by SPFA or Johns Manville.

2.5 When JM Corbond® III and JM Corbond® IV insulations are used in areas where the likelihood of termite infestation is "very heavy", they shall be installed in accordance with IBC Section 2603.9 (2009 IBC Section 2603.8) or IRC Section R318.4, as applicable.

2.5.1 When JM Corbond® III and JM Corbond® IV are used in conjunction with wood construction, in jurisdictions that have adopted NFPA 5000, and where termite infestation is known to be heavy, the foam plastic shall be installed in accordance with NFPA 5000 Section 45.6.9.5.

2.6 When used in exterior walls of buildings of Type I, II, III or IV construction, application shall be as described in Section 3.5 of this report.

3.0 PRODUCT USE

3.1 General

JM Corbond® III and JM Corbond® IV non-structural, closed cell, spray applied, polyurethane foam plastic insulations are used in wall cavities, floor assemblies, ceiling assemblies, and attics and crawl spaces. The foam plastic insulations comply with Section 2603 of the IBC, Section R316 of the IRC, and Sections C402 and R402 of the IECC (2009 IECC Sections 303 and 402) and Section 48.4 of NFPA 5000 for the specific uses described in this report. The insulation may be used in buildings of Types I, II, III, IV, or V construction per the IBC, residential structures constructed in accordance with the IRC, and buildings of Type I, II, III, IV, and V construction per NFPA 5000 when installed in accordance with Section 3.5 of this report.

3.2 Application

3.2.1 JM Corbond® III and JM Corbond® IV shall be installed by spray application using a dual component, volumetric, positive displacement proportioner to combine A- and B-components in a one-to-one volumetric ratio, as specified in the manufacturer's installation instructions.

3.2.2 JM Corbond® III and JM Corbond® IV shall not be applied to areas where the maximum service temperature is greater than 180°F (82°C). JM Corbond® III and JM Corbond® IV shall be applied to substrates that are clean, dry, and free from frost, ice, loose debris, or contaminants that will interfere with the adhesion of the spray foam insulation. JM Corbond® III and JM Corbond® IV shall not be applied in electrical outlets, junction boxes, to substrates over 120°F (49°C), or in direct contact with water, and shall be protected from the weather during application.

The product described in this Uniform Evaluation Service (UES) Report has been evaluated as an alternative material, design or method of construction in order to satisfy and comply with the intent of the provision of the code, as noted in this report, and for at least equivalence to that prescribed in the code in quality, strength, effectiveness, fire resistance, durability and safety, as applicable, in accordance with IBC Section 104.11. This document shall only be reproduced in its entirety.

Copyright © 2025 by International Association of Plumbing and Mechanical Officials. All rights reserved. Printed in the United States. Ph: 1-877-4IESRPT • Fax: 909.472.4171
web: www.uniform-es.org • 4755 East Philadelphia Street, Ontario, California 91761-2816 – USA





3.2.3 JM Corbond® III and JM Corbond® IV may be applied in passes of uniform thickness from a minimum of ½ inch (13 mm) to a maximum of 3½ inches (89 mm) per pass. The total thickness shall be as specified in Sections 3.3, 3.4, and 3.5 of this report.

“Flash” passes or a thin pass of less than 1 inch (25 mm) on cold surfaces are to be avoided and may result in loss of adhesion of subsequent passes. Thicknesses over 3½ inches (89 mm) require multiple passes in accordance with manufacturer’s installation instructions.

3.3 Thermal Barrier

3.3.1 General: JM Corbond® III and JM Corbond® IV shall be covered with a thermal barrier except as specifically excluded by the applicable code.

3.3.2 Application with a Prescriptive Thermal Barrier: JM Corbond® III and JM Corbond® IV may be applied at any thickness in ceiling cavities and in wall cavities when separated from the interior of the building by a prescriptive thermal barrier (minimum ½-inch [12.7 mm] thick gypsum board). The gypsum board shall be installed in accordance with the applicable provisions in Section 2508 of the IBC, Section R702.3 of the IRC, or Section 48.3.3 of NFPA 5000 in such a manner that the foam plastic is not exposed.

3.3.3 Alternative Thermal Barrier Assemblies: JM Corbond® III and JM Corbond® IV may be installed without a prescriptive thermal barrier when it has been installed in accordance with one of the assemblies in Table 2 of this report.

3.4 Attics and Crawl Spaces

3.4.1 General: When installing JM Corbond® III and JM Corbond® IV in attics and/or crawl spaces and a thermal barrier is omitted in accordance with IBC Section 2603.4.1.6, IRC Sections R316.5.3 or R316.5.4 or Section 48.3.3.4 of NFPA 5000, installation shall comply with either Sections 3.4.2 or 3.4.3 of this report.

JM Corbond® III and JM Corbond® IV spray-foam insulations qualify as an air-impermeable insulation and, when installed in accordance with Sections 3.4.2 or 3.4.3 of this report, may be used to insulate unvented attics and/or unvented cathedral ceilings in accordance with 2021, 2018, and 2015 IRC Section R806.5 (2012 and 2009 IRC Section R806.4).

3.4.2 Application with a Prescriptive Ignition Barrier: When JM Corbond® III and JM Corbond® IV insulations are installed within attics and crawl spaces where entry is made only for service of utilities, the insulation, at a maximum of 4 inches (102 mm) thick, shall be covered with a prescriptive ignition barrier in accordance with IBC Section 2603.4.1.6, IRC Sections R316.5.3 and R316.5.4, or Section 48.3.3.4 of NFPA 5000, as applicable. The ignition barrier shall be

consistent with the construction type of the building. The ignition barrier shall be installed in accordance with the provisions applicable to the material referenced in the IBC, IRC, or NFPA 5000 in such a manner that the foam plastic is not exposed.

Exception: The prescriptive ignition barrier may be omitted when installed in accordance with Section 3.4.3.

3.4.3 Application with an Alternative Ignition Barrier Assembly: The spray-applied foam plastic insulation may be installed without a prescriptive ignition barrier in accordance with Sections 3.4.3.1, 3.4.3.2, or 3.4.3.3 of this report, when all of the following conditions apply, as applicable:

- Entry to the attic or crawl space is only to service utilities, and no storage is permitted.
- Attic ventilation is provided when required by 2021 and 2018 IBC Section 1202.2, 2015 IBC Section 1203.2, or IRC Section R806, except when an air-impermeable insulation is permitted in unvented attics in accordance with Section R806.4 of the IRC. Under-floor (crawl space) ventilation is provided when required by 2021 and 2018 IBC Section 1202.4, 2015 IBC Section 1203.4 (2012 and 2009 IBC Section 1203.3), or IRC Section R408.1, as applicable.
- The foam plastic insulation is limited to the maximum thickness and density stated in this report.
- Combustion air is provided in accordance with the Uniform Mechanical Code (UMC) Section 701.1 or International Mechanical Code (IMC) Section 701, as applicable.
- The installed coverage rate or thickness of coatings, if part of the insulation system, shall be equal to or greater than that which was tested.
- Attic and crawl spaces do not have interconnected areas.
- Air in the attic or crawl space is not circulated to other parts of the building.

3.4.3.1 Attic and Crawl Space Overhead and Vertical Surfaces Covered with an Alternative Ignition Barrier: JM Corbond® III and JM Corbond® IV spray foam insulations may be spray-applied without a prescriptive ignition barrier to overhead surfaces and/or vertical surfaces when covered with an alternative ignition barrier as described in Sections 3.4.3.1.1 or 3.4.3.1.2 (and as summarized in Table 5) of this report.

3.4.3.1.1 JM IC Ignition Barrier: Surfaces to be coated shall be dry, clean, and free of dirt, loose particles and any other substances that could interfere with adhesion of the coating. Back-rolling of sprayed material may be necessary to fill pinholes in substrates. The JM IC Ignition Barrier shall be applied with a medium-size nap roller, soft brush, or conventional airless spray equipment to a minimum dry film thickness of 3 mils (0.08 mm) (requiring an application rate of approximately 4 wet mils [0.10 mm] or 345 ft²/gal [8.3 m²/L]). The coating shall be applied in accordance with the JM



IB Product Data Sheet and this report. The maximum thickness of JM Corbond III® and JM Corbond® IV is limited to 5½ inches (140 mm) on overhead surfaces and 3½ inches (89 mm) on vertical surfaces.

3.4.3.1.2 JM Spider® with Adhesive: JM Spider® with adhesive shall be installed by insulation contractors who have been trained and certified by Johns Manville. Installers shall use only the JM Spider® Insulation Delivery System equipment engineered and specified by Johns Manville. JM Spider® with adhesive shall be applied in accordance with Johns Manville installation specifications. If the installation temperatures are below 50°F (10°C), the adhesive shall be heated and applied per Johns Manville specifications. JM Spider® with adhesive spray-on insulation shall be installed at a minimum 2½ inches (63.5 mm) thickness and a nominal density of 1.8 pcf (28.8 kg/m³). The maximum thickness of JM Corbond III® and JM Corbond® IV is limited to 10 inches (254 mm) on overhead surfaces and 8 inches (203 mm) on vertical surfaces.

3.4.3.2 Attic Floors: JM Corbond® III and JM Corbond® IV insulations may be installed exposed (no coating), without an ignition barrier up to a maximum thickness of 11½ inches (292 mm) between and over the joist in attic floors. The insulation shall be separated from the interior of the building by a minimum ½-inch (12.7 mm) thick gypsum board or an approved equivalent thermal barrier, which shall be installed in accordance with the provisions set forth in the IBC, IRC, or evaluation report. The ignition barrier required by IBC Section 2603.4 and IRC Section R316.5.3 may be omitted in this case.

3.4.3.3 Attic and Crawl Space Overhead and Vertical Surfaces Without an Ignition Barrier: The JM Corbond® III and JM Corbond® IV may be installed exposed (no coating), without an ignition barrier when installed as required in this section. JM Corbond® III and JM Corbond® IV insulations may be spray-applied in attics to the underside of roof sheathing, roof rafters, and vertical surfaces, and in crawl spaces to the underside of floors and vertical surfaces. When applied to the underside of the top of the space, the thickness of the JM Corbond® III and JM Corbond® IV insulations shall not exceed 7½ inches (191 mm) and when applied to vertical surfaces, the maximum thickness shall not exceed 5½ inches (140 mm).

3.5 Exterior Walls of Types I, II, III, and IV Construction (IBC)

3.5.1 When used on exterior walls of Type I, II, III, and IV construction, JM Corbond® III and JM Corbond® IV spray-applied foam insulation shall comply with Section 2603.5 of the IBC or Section 48.4.1 of NFPA 5000, as applicable, and Section 3.5.2 of this report, and shall be installed at a maximum thickness of 3½ inches (88.9 mm). The potential heat of the JM Corbond® III and JM Corbond® IV is 1991 BTU/ft² (22.4 MJ/m²) per inch of thickness when tested in accordance with NFPA 259.

3.5.2 Specific Wall Assemblies: Wall assemblies shall be constructed as described in Tables 3 and 4 of this report. Walls required to be fire resistance rated construction are beyond the scope of this report and shall comply with IBC Section 2603.5.1.

3.6 Installation

3.6.1 Installation General: JM Corbond® III and JM Corbond® IV shall be installed in accordance with the manufacturer's installation instructions, the applicable code, and this report. The installation instructions and this report shall be made available upon request.

4.0 PRODUCT DESCRIPTION

4.1 General

4.1.1 JM Corbond® III and JM Corbond® IV are two-component, spray-applied, medium-density, closed-cell polyurethane foam plastic insulation systems having a nominal core density of 2.0 pcf (32 kg/m³). The foam plastic is generated by combining the isocyanate (A-component) and a polymeric resin (B-component) through a dual component proportioner, on site, by SPFA certified or Johns Manville certified applicators. All materials shall be stored in their original containers, which shall be kept out of direct sunlight and away from heat and moisture. When stored unopened and indoors at a temperature between 50°F (10°C) and 80°F (27°C), the shelf life for A-component isocyanate is 12 months, and B-component polymeric resin is 9 months. Prior to use, both components (A and B) shall be conditioned in a manner that results in drum temperatures between 60°F (16°C) and 75°F (24°C).

4.1.2 A-component isocyanate and B-component polymeric resin properly mixed and applied yields a Lavender® finished foam insulation product. The Lavender® color is a Federal Registered Trademark color of Johns Manville.

4.2 Surface Burning Characteristics

4.2.1 JM Corbond® III and JM Corbond® IV, when tested in accordance with ASTM E84 at a maximum thickness of 4 inches (102 mm) and a nominal core density of 2.0 pcf (32 kg/m³), has a flame spread index of less than 25 and a smoke developed index of not more than 450.

4.2.2 Thicknesses are not limited for ceiling cavities and wall cavities when covered by a prescriptive thermal barrier (minimum ½-inch [12.7 mm] thick gypsum board) in accordance with Section 3.3.2 of this report. Thicknesses of up to 11½ inches (292 mm) for ceiling or floor cavities and 7½ inches (191 mm) for wall cavities are recognized based on testing in accordance with NFPA 286, when installed in accordance with Section 3.3.3 of this report.

4.3 Thermal Resistance: The R-value of JM Corbond® III and JM Corbond® IV is 7.0 °F.ft².h/Btu per inch regardless of



thickness. Table 1 of this report provides additional information on the values of thermal resistance (R-Value) for specific thicknesses.

4.4 Water Vapor Resistance: JM Corbond® III and JM Corbond® IV, when tested in accordance with Procedure A of ASTM E96, has a vapor permeance of less than 1 perm (57 ng/Pa-s-m^2) at a minimum thickness of 1.5 inches (38 mm), and qualifies as a Class II vapor retarder as defined in IBC Section 202, IRC Section R202, 2021 and 2018 NFPA 5000 Section 3.3.668, and 2015 NFPA 5000 Section 3.3.662.1 (2012 and 2009 NFPA 5000 Section 3.3.644.1).

4.5 Air Permeability: JM Corbond® III and JM Corbond® IV, when tested in accordance with ASTM E283 at a minimum thickness of 1.0 inch (25.4 mm), exhibit a maximum total air leakage rate of 0.02 L/s-m^2 ($0.004 \text{ ft}^3/\text{min-ft}^2$) when tested at a 75 Pa pressure differential and qualifies as an air-impermeable insulation for use in attics in accordance with the applicable code.

4.6 Fungal Resistance: JM Corbond® III and JM Corbond® IV, when tested in accordance with ASTM C1338, exhibit no fungal growth.

4.7 Fire Protective Coatings

4.7.1 JM IC (aka TPR² Fireshell® IB4): JM IC ignition barrier coating is manufactured by Thermal Products Research (TPR2). The coating is water-based and available in both 5-gallon (18.9 L) and 55-gallon (208 L) containers and has a shelf life of 12 months when stored in factory-sealed containers above 45°C (7°C).

4.7.2 JM TC (aka Fireshell® F10/E/TB): JM TC thermal barrier coating is manufactured by Thermal Products Research (TPR2). The coating is water-based and available in both 5-gallon (18.9 L) and 55-gallon (208 L) containers and has a shelf life of 12 months when stored in factory-sealed containers above 45°C (7°C).

4.7.3 DC315 Fireproof Paint: DC315 Fireproof Paint, recognized in [ER-499](#), is a water-based latex intumescent coating manufactured by International Fireproof Technology, Inc. and is supplied in 5-gallon (19 L) pails and 55-gallon (208 L) drums. When stored in factory-sealed containers at temperatures between 50°F (10°C) and 80°F (27°C), the coating has a shelf life of 12 months.

4.7.4 No-Burn® Plus ThB Coating: No-Burn Plus ThB coating, recognized in [ER-305](#), is a water-based latex liquid manufactured by No-Burn, Inc., which exhibits intumescent properties when exposed to elevated temperatures and flame. The product is packaged in 5-gallon pails and 55-gallon drums and has a shelf life of eighteen months when stored in unopened containers between 40°F and 90°F.

4.8 JM Spider® Ignition Barrier

4.8.1 JM Spider® ignition barrier is supplied by Johns Manville Corporation. The JM Spider® loose-fill glass fiber material is mixed with an adhesive during the spraying process and adheres to the foam plastic. The JM Spider® is available in 30 lb (13.6 kg) bags. The ignition barrier shall be kept clean and dry at all times. The spray-applied fiberglass product may be installed at variable thickness levels and may be used for both wall and ceiling applications.


4.8.2 The JM Spider® adhesive comes in totes and 55-gallon (208 L) drums. The adhesive shall be stored in a cool, dry area in original packaging and at temperatures above 40°F (4.4°C).

5.0 IDENTIFICATION

Jobsite labeling and certification of the insulation shall comply with IRC Sections N1101.10 and 1101.10.1 (2012 IRC Sections 1101.12 and 1101.12.1 and 2009 IRC Sections N1101.4 and N1101.4.1), and IECC Sections C303.1.1 and C303.1.2, R303.1.1 and R303.1.2, as applicable. Each component for the JM Corbond® III and JM Corbond® IV is identified with the following:

- Manufacturer's name (Johns Manville), address and telephone number.
- Product trade name (JM Corbond® III and JM Corbond® IV).
- Product density.
- Flame-spread and smoke-development indices
- Evaluation report number (ER-146)

Either IAPMO UES Mark of Conformity may also be used as shown below:



IAPMO UES ER-146

6.0 SUBSTANTIATING DATA

6.1 Data in accordance with ICC-ES Acceptance Criteria for Spray-Applied Foam Plastic Insulation (AC377) Approved April 2020 (editorially revised July 2020).

6.2 Reports on air leakage tests in accordance with ASTM E283.

6.3 Reports on water vapor transmission tests in accordance with ASTM E96.



6.4 Reports on Fungal Resistance tests in accordance with ASTM C1338.

6.5 Reports on flame spread and heat release in accordance with NFPA 286.

6.6 Reports on Exterior Fire Propagation tests in accordance with NFPA 285.

6.7 Reports on Potential Heat tests in accordance with NFPA 259.

6.8 Reports on Heat Release and Flame Propagation in accordance with AC377 Appendix X.

6.9 Test Reports are from Laboratories in conformance with ISO/IEC 17025.

7.0 STATEMENT OF RECOGNITION

This evaluation report describes the results of research carried out by IAPMO Uniform Evaluation Service on Johns Manville's JM Corbond® III and JM Corbond® IV to assess their conformance to the codes shown in Section 1.0 of this report and serves as documentation of the product's certification. Products are manufactured under a quality control program with periodic inspections under the supervision of IAPMO UES.

For additional information about this evaluation report please visit www.uniform-es.org or email us at info@uniform-es.org

TABLE 1: THERMAL RESISTANCE (R-Value)¹

Thickness (Inch)	R-Value (°F.ft ² .hr/Btu)
1.0	7.0
2.0	14
3.0	21
3.5	24.5
4.0	28
5.0	35
5.5	38.5
6.0	42
7.0	49
8.0	56
9.0	63
10.0	70
11.0	77
12.0	84

For SI: 1 inch= 25.4 mm; 1 °F.ft².hr/Btu =0.176110 °K.m²/W.

¹ R-values are calculated based on tested k-factors at 1- and 4-inch thicknesses



TABLE 2: ALTERNATE ASSEMBLIES WITHOUT A PRESCRIPTIVE THERMAL BARRIER^{1,2}

Coating	Max. Insulation Thickness Overhead Surfaces	Max. Insulation Thickness Vertical Surfaces	Dry Film Thickness	Wet Film Thickness (nominal)	Application Rate ¹ (theoretical)
JM TC (aka FIRESHIELD® F10E)	11.5 in. 292 mm	7.5 in. 191 mm	12 mils 0.30 mm	18 mils 0.46 mm	86 ft ² /gal 2.11 m ² /L
DC315	11.5 inches 292 mm	7.5 inches 191 mm	9 mils 0.23 mm	14 mils 0.36 mm	115 ft ² /gal 2.82 m ² /L
Plus ThB	8 inches 203 mm	6 inches 152 mm	9 mils 0.23 mm	14 mils 0.36 mm	115 ft ² /gal 2.82 m ² /gal

Notes:

¹ Theoretical coating application rates are based strictly on minimum wet film thickness requirements and shall be increased for site-specific conditions such as foam plastic surface texture, overspray loss, container and other residues, application technique and environmental conditions.

² The coatings shall be applied in accordance with the Product Data Sheet and this report in such a manner that the foam plastic is not exposed.

TABLE 3: NFPA 285 COMPLYING WALL ASSEMBLIES WITH JM CORBOND III® AND JM CORBOND® IV IN WALL CAVITY

WALL COMPONENTS	MATERIALS
Base Wall System ¹ (Use either 1, 2 or 3)	- Concrete wall - Concrete masonry wall 1 layer of 5/8-inch thick Type X gypsum wallboard installed on the interior side of minimum 35/8-inch deep, minimum 25-gauge equivalent thick steel studs spaced a maximum of 24 inches on center. Lateral bracing installed minimum every 4 feet vertically or as required. Wall stud cavities shall be filled at each floor line with minimum 4 lb/ft³ mineral wool (e.g. JM MinWool® Safing) friction fit between steel wall studs.
Perimeter Fire Barrier System	Perimeter fire barrier system complying with Section 715.4 of the 2015 IBC shall be installed, as applicable, to fill the void between the edge of the concrete floor slab and the interior surface of the exterior wall assembly (see note 1).
Interior Insulation (Use either 1, 2, 3, 4, 5 or 6)	- None - Maximum 35/8-inch thickness of JM Corbond® III or JM Corbond® IV CC SPF applied to interior surface of Base Wall System 1 and 2 (See Note 1). - Full wall stud cavity depth or less of JM Corbond® III or JM Corbond® IV CC SPF applied using exterior gypsum sheathing of Base Wall System 3 as the substrate and covering the width of the cavity and the inside of the steel wall stud framing flange. - Fiberglass batt insulation (faced or unfaced) - Mineral wool insulation (faced or unfaced) - Hybrid Systems: spray foam and/or fiberglass insulation or mineral wool insulation (flash and bat insulation systems)
Exterior sheathing	5/8-inch-thick Type X exterior gypsum sheathing (for Base Wall System 3 above)
Exterior Wall Covering ²	Any non-combustible exterior wall covering material using any standard installation technique
Window Closure	Minimum 0.08-inch-thick aluminum, or equivalent
Flashing of window, door and other exterior wall penetrations	As an option, flash around window, door, and other exterior penetrations with limited amounts of maximum 12-inch-wide flashing tape (acrylic, asphalt or butyl-based) or liquid applied membrane material with or without fiber mesh reinforcement.

For SI: 1 inch= 25.4 mm; 1.0 pcf =16 kg/m³

Notes:

¹ Fireblocking per IBC Section 718 (2009 IBC Section 717) and thermal barrier material requirements shall be met for Base Wall Systems 1 and 2, as required by specific wall construction details when combustible concealed space is created on interior side of exterior wall assembly.

² Non-combustible exterior wall coverings shall be installed in accordance with manufacturer's installation requirements.



TABLE 4: NFPA 285 COMPLYING WALL ASSEMBLIES WITH CORBOND III® INSTALLED ON THE EXTERIOR

WALL COMPONENTS	MATERIALS
Base Wall System ¹ (Use either 1, 2 or 3)	1. Concrete wall 2. Concrete masonry wall 3. 1 layer of 5/8-inch thick Type X gypsum wallboard installed on the interior side of minimum 3 5/8-inch deep, minimum 25-gauge equivalent thick steel studs spaced a maximum of 24 inches on center. Lateral bracing installed minimum every 4 feet vertically or as required. Wall stud cavities shall be filled at each floor line with minimum 4 lb/ft³ mineral wool (e.g. JM MinWool® Safing) friction fit between steel wall studs.
Perimeter Fire Barrier System	Perimeter fire barrier system complying with Section 715.4 of the 2015 IBC shall be installed, as applicable, to fill the void between the edge of the concrete floor slab and the interior surface of the exterior wall assembly (see note 1).
Interior Insulation (Use either 1, 2, 3, 4, 5 or 6)	1. None 2. Maximum 3 5/8-inch thickness of JM Corbond® III or JM Corbond® IV CC SPF applied to interior surface of Base Wall System 1 and 2 (See Note 2). 3. Full wall stud cavity depth or less of JM Corbond® III or JM Corbond® IV CC SPF applied using exterior gypsum sheathing of Base Wall System 3 as the substrate and covering the width of the cavity and the inside of the steel wall stud framing flange. 4. Fiberglass batt insulation (faced or unfaced) 5. Mineral wool insulation (faced or unfaced) 6. Hybrid Systems: spray foam and/or fiberglass insulation or mineral wool insulation (flash and bat insulation systems)
Exterior Sheathing (Use either 1, 2 or 3)	1. None (for Base Wall Systems 1 or 2 above) 2. 1/2-inch thick glass mat exterior gypsum sheathing complying with ASTM C1177 (for Base Wall System 3 above) 3. 5/8-inch-thick Type X exterior gypsum sheathing (for Base Wall System 3 above)
Exterior Insulation	Maximum 3 1/2-inch thickness of JM Corbond® III or JM Corbond® IV CC SPF
Exterior Wall Covering (Use either 1, 2, 3, 4 or 5)	1. Brick – Standard type brick veneer anchors, installed a maximum of 24 inches on center, vertically on each stud with maximum 1-inch air gap between exterior insulation and brick. Brick to be standard nominal 4-inch-thick clay brick installed in a running bond pattern using Type S mortar. 2. Stucco – Minimum 3/4-inch thick, exterior cement plaster and lath. A secondary water-resistive barrier (WRB) may be installed between the exterior insulation and the lath. The secondary WRB shall not be full-coverage asphalt or butyl-based self-adhered membranes. 3. Minimum 2-inch-thick natural stone (granite, limestone, marble, sandstone). Any standard non-open jointed installation technique may be used. 4. Minimum 1 1/2-inch thick concrete masonry unit (CMU), precast concrete, or artificial cast stone. Any standard non-open jointed installation technique may be used. 5. Minimum 1 1/4-inch thick Terra Cotta non-opened jointed. Any standard non-open jointed installation technique may be used.
Window Closure	No. 14 gauge (0.078 inch) (or thicker) steel flashing, or equivalent
Flashing of window, door and other exterior wall penetrations	As an option, flash around window, door and other exterior penetrations with limited amounts of maximum 12-inch-wide flashing tape (acrylic, asphalt or butyl-based) or liquid applied membrane material with or without fiber mesh reinforcement.

For SI: 1 inch= 25.4 mm; 1.0 pcf =16 kg/m³

Notes:

¹ Fireblocking per IBC Section 718 (2009 IBC Section 717) and thermal barrier material requirements shall be met for Base Wall Systems 1 and 2, as required by specific wall construction details when combustible concealed space is created on interior side of exterior wall assembly.

**TABLE 5: ALTERNATE IGNITION BARRIER ASSEMBLIES**

Coating/Cover	Max. Insulation Thickness Overhead Surfaces	Max. Insulation Thickness Vertical Surfaces	Dry Film Thickness	Wet Film Thickness (nominal)	Application Rate (nominal)
JM IC Ignition Barrier Coating (aka Fireshell® IB4)	5½ inches 140 mm	3½ inches 89 mm	3 mils 0.08 mm	4 mils 0.1 mm	345 ft ² /gal 8.3 m ² /L
JM Spider®	10 inches 254 mm	8 inches 203 mm	2.5 inches 64 mm	NA	NA

Notes:

NA = Not Applicable