



Formaldehyde-free™ Blow-in Loose-fill Fibre Glass Insulation

**ATTIC
PROTECTOR®**

PRODUCT DATA SHEET

COMPANY

JM Formaldehyde-free™ fibre glass building insulation offers the thermal and acoustical performance you expect from fibre glass—and it improves indoor air quality because it’s made without formaldehyde. Why is that important? Because reducing overall formaldehyde levels in the home creates a healthier living environment, and choosing JM Formaldehyde-free™ insulation is one way of achieving that goal. JM offers the only complete line of certified Formaldehyde-free™ fibre glass home insulation. Visit www.JM.com for more information.

DESCRIPTION

Johns Manville Attic Protector® is premium blow-in fibre glass insulation that can be used to cover attics and hard-to-reach areas within attics, like corners, edges and around framing. When it’s applied in an air-sealed attic to the recommended thickness and specifications, you can be assured that your attic is energy efficient, with minimal heat loss. Attic Protector won’t appreciably settle, decay or provide food for animals or microbes. It’s effective for the life of your home.

USE

Attics – can be installed up to R-70 over ½" ceiling drywall without exceeding ceiling weight limits.

INSTALLATION

Attic Protector fibre glass makes it easy to insulate an attic of any size or shape without any cutting or fitting. It’s installed with a blowing machine and flexible hose, making it easy to insulate hard-to-reach areas in an attic. Large areas and small gaps can be filled quickly and completely.

PACKAGING

Attic Protector insulation is compression-packaged for savings in storage and freight costs.

DESIGN CONSIDERATIONS

Store insulation indoors. Keep insulation clean and dry at all times. When transporting, cover completely with a waterproof tarpaulin as necessary.

Refer to the JM guide specifications for further design considerations and required installation instructions.

LIMITATIONS OF USE

Check applicable building codes.



PERFORMANCE ADVANTAGES

Formaldehyde-Free: will not off-gas formaldehyde in the indoor environment.

Thermal Efficiency: provides effective resistance to heat transfer.

Sound Control: reduces transmission of sound through ceiling assemblies.

Fire Resistant and Noncombustible: see Specification Compliance.

Resilient Inorganic Glass: will not rot, mildew or deteriorate and is noncorrosive to pipes, wiring and metal studs.

Complete Coverage: effective in tight spaces, areas with large amounts of cross-bridging and areas with small gaps and voids.

ENERGY AND ENVIRONMENT





Formaldehyde-free™ Blow-in Loose-fill Fibre Glass Insulation



PRODUCT DATA SHEET

ATTIC PROTECTOR®

APPLICABLE STANDARDS & BUILDING CODE CLASSIFICATION**

ATTIC PROTECTOR

CAN/ULC-S702-09, Type 5

CAN/ULC-S102.2 Flame Spread 25 or less, Smoke Developed 50 or less

ULC-S129 Smoulder Resistance – Pass

CCMC 12642-L

** JM insulations comply with IBC (International Building Code), model code requirements for building construction types listed above.

ATTIC PROTECTOR CHART†

THERMAL RESISTANCE		BAGS PER UNIT AREA		MINIMUM THICKNESS		MAXIMUM COVERAGE‡ PER BAG		MINIMUM MASS PER UNIT AREA	
To obtain an installed thermal resistance of:		The number of bags per 100 m ² /1000 ft ² of net area shall not be less than:		Insulation/Cavity Thickness		Contents of this bag shall not cover more than:		The weight per m ² /ft ² of installed insulation shall not be less than:	
RSI	R	100 m ²	1000 ft ²	mm	Inches	m ²	ft ²	kg/m ²	lb/ft ²
1.8	10	6.6	6.2	102	4.00	15.1	162.2	0.81	0.17
2.1	12	7.8	7.2	114	4.50	12.9	139.0	0.95	0.19
2.8	16	10.3	9.6	152	6.00	9.7	104.3	1.26	0.26
3.5	20	12.9	12.0	191	7.50	7.7	83.4	1.58	0.32
4.2	24	15.5	14.4	226	8.88	6.5	69.5	1.89	0.39
4.9	28	18.1	16.8	264	10.38	5.5	59.6	2.21	0.45
5.6	32	20.7	19.2	302	11.88	4.8	52.1	2.52	0.52
6.3	36	23.3	21.6	340	13.38	4.3	46.3	2.84	0.58
7.0	40	25.8	24.0	378	14.88	3.9	41.7	3.15	0.64
7.7	44	28.4	26.4	416	16.38	3.5	37.9	3.47	0.71
8.4	48	31.0	28.8	454	17.88	3.2	34.8	3.78	0.77
8.8	50	32.5	30.1	476	18.75	3.1	33.2	3.96	0.81
9.1	52	33.6	31.2	492	19.38	3.0	32.1	4.10	0.84
9.8	56	36.2	33.6	530	20.88	2.8	29.8	4.41	0.90
10.5	60	38.8	36.0	568	22.38	2.6	27.8	4.73	0.97
11.2	64	41.3	38.4	603	23.75	2.4	26.1	5.04	1.03

† Coverage without framing.

‡ The manufacturer recommends that the insulation be installed at these minimum thicknesses and maximum coverages to provide the levels of insulation thermal resistance (R-value) shown (based on 26.9 lb. average net weight per bag).

*GREENGUARD certification is not intended for residential environments. Instead, the certification is intended only for buildings meeting ASHRAE 62.1-2007 commercial building ventilation rates. This certification is proof that the product meets the GREENGUARD Environmental Institute's indoor air quality standards and product emission standards for VOCs.



Visit our website at www.JM.com or call **1-800-654-3103** | **Building Insulation Division** P.O. Box 5108 | Denver, CO 80217-5108

Technical specifications as shown in this literature are intended to be used as general guidelines only. The physical and chemical properties of thermal and acoustical fibre glass insulation listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the sales office nearest you for current information. All Johns Manville products are sold subject to Johns Manville's Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville Limited Warranty and Limitation of Remedy or for information on other Johns Manville thermal and acoustical insulation and systems, visit the website or call the 800 number above. 717 17th Street Denver CO, 80202

CAN-355 9/14

© 2014 Johns Manville. All Rights Reserved.