

COMPANY

Johns Manville, a Berkshire Hathaway company, was founded in 1858. Our ownership by Berkshire Hathaway, one of the most admired companies in the world and one of the most financially secure, allows JM to invest for the future. This enables JM to continue delivering the broadest range of insulation products in the industry and offering innovative solutions that meet your needs.

DESCRIPTION

Johns Manville Window & Door Polyurethane Foam Sealant (“JM Window & Door”) is a closed cell, low pressure one-component foam sealant. JM Window & Door will not bow or distort windows or doors and is designed to resist moisture and mold problems.

RECOMMENDED USE

JM Window & Door is designed to seal openings around doors and windows. It is for professional use ONLY. It is chemically inert and non-reactive in approved applications, and will not harm electrical wire insulations, rubber, PVC, or other plastics. This product is not resistant to UV rays and should be painted or coated if it will be exposed.

APPLICATION

JM Window & Door is meant to be installed at temperatures between 65-80°F. Substrate must be clean, dry, and free of loose particles, dust, grease and mold released agents. Product is to be applied without thinning.

Review instruction panel on can. To apply, attach the can to the dispensing gun (available separately from Johns Manville), shake well, and pull the gun trigger to dispense. The dispensing guns can be controlled by varying the amount of pressure applied to the trigger, or by using the metering screw located in the back. Application can be interrupted when needed as outlined in the instructions and the dispensing gun will be ready for immediate reuse, as long as it remains attached to a pressurized container. An empty gun foam container must be replaced with a new container.

PRODUCT STORAGE

Store upright in a dry area and do not expose the product to open flame or temperatures above 122°F. Storage in excessive heat can cause premature aging, resulting in a shorter shelf-life. Shelf-life is 15 months from date of manufacture (see date located on bottom of each can).



PERFORMANCE ADVANTAGES

- Low pressure: will not bow or distort window
- Resists moisture and mold
- Air sealing is critical to an energy efficient home

SPECIFICATION COMPLIANCE AND PHYSICAL PROPERTIES

Technical Data	Standard	Results
Density - Gun Foam	ASTM D 1622	1.00 lbs/ft ³ (16 kg/m ³)
K-factor	ASTM C 518	0.213 Btu-in/ft ² • h • °F
R-Value	ASTM C 518	4.70 per inch
Air Permeability @ 1.57 psf (75 Pa)	ASTM E 283	< 0.00028 cfm/ft ² (< 0.0014 L/s/m ²)
Compressive Strength - <i>parallel to rise</i>	ASTM D 1621	6.38 psi (43.9 kPa)
Durability	CAN/ULC 710.1	Pass
Dimensional Stability	ASTM D 2126	+/- 5%
Tack-Free	Tack-Free	Approx. 5 minutes
Closed-Cell Content	ASTM D 2856	68%
Cutable	-	1 Hour
Fire Rating - Caulking & Sealant Tested 3 Beads @ 3/4" Thickness	CAN/ULC S102	Flame Spread Index < 25 Smoke Developed < 50
Fire Rating - Caulking & Sealant Tested 3 Beads @ 3/4" Thickness	ASTM E84/UL 723	Flame Spread Index < 25 Smoke Developed < 50

APPROVALS/STANDARDS/CLASSIFICATIONS

ASTM E84/UL 723	UL Classified File R-39012
NFPA 30B	Level 2 Aerosol
VOC Content (calculated minus exempt compounds)	165 g/L or 16%
AAMA 812	Tested in accordance
ASTM E2112	Section 5.9.2
CSA A440.4	

TEMPERATURE

Product Storage	<122°F (50°C)
Application	40-100°F (5-38°C)
Chemical	65-80°F (18-27°C)

YIELD* (1.00 Density); Linear Feet (Meters)

	1/4" (6.3mm)	3/8" (9.5 mm)	1/2" (12.7 mm)	Volume
24oz (680g) Gun Foam	4403 ft (1342 m)	1957 ft (596 m)	1101 ft (336 m)	1.50 ft ³ (42 L)

*Yield is based on density. We state our core density when describing the foam. We use theoretical calculations for comparative purposes so the results will vary depending on ambient conditions and use in particular applications.