



PRODUCT DATA SHEET

DESCRIPTION

JM IC (Johns Manville Ignition Coating), also known as Fireshell® IC is a single-component, water-based intumescent coating designed for application as an ignition barrier over JM open and closed-cell spray foam products in attics and crawlspaces. JM IC is formulated for application over polyurethane foam to reduce heat transfer and surface burning in the event of a fire.

UNIQUE PROPERTIES

JM IC is formulated to adhere to polyurethane foam and a variety of other substrates. JM IC, when installed properly, will serve in lieu of an otherwise code-prescribed ignition barrier.

GENERAL APPLICATION INSTRUCTIONS

JM IC may be applied by medium-nap rollers, brushes or conventional or airless spray equipment designed to handle a tip size of 0.021 inches. Airless spray application is most efficient, whereas rolling or brushing may be used for touch-ups. CONTACT JM TECHNICAL SERVICE PERSONNEL FOR SPECIFIC RECOMMENDATIONS, PRICING AND AVAILABILITY. Apply JM IC only to clean, dry, sound surfaces, free of loose particles or other foreign matter that may interfere with the adhesion of the coating. Backrolling sprayed material may be necessary to fill pinholes in coating. Final cured dry film thickness should be free of excessive voids, pinholes, holidays, cracks or blisters. COATING APPLICATION SHOULD BE SUSPENDED IMMEDIATELY AND JM TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS OBTAINED ARE LESS THAN DESIRABLE.



To be an effective ignition barrier, JM IC should be applied to JM ocSPF at a minimum application rate of 1 gallon per 230 square feet and minimum dry film thickness of 4 mils (4 mils equates to a wet film thickness of 7 mils). Rough surface profiles, which increase total surface, will require a proportionate increase in the amount of JM IC to satisfy specified minimum dry mil thickness. To be an effective ignition barrier, JM IC should be applied to JM Corbond closed-cell products at a minimum application rate of 1 gallon per 330–375 square feet and minimum dry film thickness of 4 mils (4 mils equates to a wet film thickness of 7 mils). Rough surface profiles, which increase total surface, will require a proportionate increase in the amount of JM IC to satisfy specified minimum dry mil thickness.

Limitations and Precautions

JM IC is a water-based intumescent coating that will freeze and become unusable at temperatures below 32°F.

Protect from Freezing During Shipment and Storage. Do not store material at temperatures below 45°F. Do not apply JM IC when ambient air and substrate temperatures fall below 55°F or when there is a possibility of temperature dropping below 32°F within a 24-hour period after application.

Do not apply over wet substrates. Total cure of JM IC requires complete evaporation of water. Cool temperatures and high humidity retard cure. Therefore, do not apply if weather conditions prevent complete cure before freezing temperatures. JM IC is not a vapor barrier coating and not recommended for use over most cold storage installations. Where a vapor barrier is required, contact JM Technical Service Personnel for proper selection and installation procedures.

JM IC Ignition Barrier Coating General Safety, Toxicity, Health Data

Material Safety Data Sheets are available on this coating material. Any individual who comes in contact with these products should read and understand the MSDS.

Cleanup: Water

Eye Protection: Safety glasses, goggles or a face shield are recommended.

Skin Protection: Chemical-resistant gloves are recommended. Cover as much of the exposed skin as possible with appropriate clothing.

Respiratory Protection Is Mandatory! Respiratory protective equipment, impervious footwear and protective clothing are required at all times during spray application.

Ingestion: Do not take internally. Consider the application and environmental concentrations in deciding if additional protective measures are necessary.



JM IC IGNITION BARRIER INTUMESCENT COATING FOR JM SPRAY FOAM

FIRESHELL® IC

PRODUCT DATA SHEET

PHYSICAL PROPERTIES

Volatiles/VOC(g/l)	Below 50 g/l SCAQMD & EPA
Flame Spread & Smoke	ASTM E84 Class 1 (<25fs, <50s)
Solvents, Toxicity	None, water based, nontoxic
Environmental Impact	Green product per greenguide.com
Weight per Gallon	11.5lbs ± 0.3lbs
Colors	Off white
Application Time	JM IC may be applied to SPF as quickly as the core temperature of the foam has returned to ambient room temperature.
Dry Times	To touch 90 minutes, 1–2 hours between coats, see Drying Conditions below
Drying Conditions*	- cross-ventilation always required - mechanically dehumidify if 60 percent rh or greater is present - fully cures in three weeks
Recommended Equipment	Airless: Graco 695–2200psi at tip with 3/8" line Gun: Graco HD texture gun p/n 241705 Tips: 0.023 to 0.025
Sag Resistance	35+ mils walls, 20+ mils on ceilings (for reference)
Mold & Fungi Resistance	ASTM 3273 Excellent
Spraying Temps	55°–95°F ambient interior, coating must be kept above 62°F
Container sizes	5 gallon pails or 55 gallon drums
Shelf Life	1 year from date of manufacture, store above 45°F
Washability	ASTM D2486 Scrub Resistance > 1100 cycles ASTM D4585 Moisture Resistance, 100 hours

*See www.tpr2.com "ventilation procedure."

RECOMMENDED WFT-DFT, COVERAGE RATES, WALL & CEILING FOAM THICKNESSES:

FOAM	WFT mils	DFT mils	SF/gal	WALL	CEILING
JM OC SPF	7	4	230	7½"	9½"
JM CORBOND III AND MCS	4	3	330-375	3½"	5½"

DISCLAIMER

The data presented herein is not intended for use by nonprofessional applicators or those persons who do not purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

All guarantees and warranties as to products supplied by Johns Manville shall have only those guarantees and warranties expressed by the manufacturer. Buyer's sole remedy as to any material claims will be against the manufacturer of the product. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE, ARE MADE BY JM WITH RESPECT TO PRODUCTS OR INFORMATION SET FORTH HEREIN. Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Johns Manville and the manufacturer of all liability with respect to the materials and their use thereof.



Visit our website at specJM.com or call **1-800-654-3103** | Building Insulation Division P.O. Box 5108 | Denver, CO 80217-5108

Technical specifications as shown in this literature are intended to be used as general guidelines only. The physical and chemical properties of intumescent coating listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the sales office nearest you for current information. All Johns Manville products are sold subject to Johns Manville's Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville Limited Warranty and Limitation of Remedy or for information on other Johns Manville ignition and acoustical insulation and systems, visit the website or call the 800 number above. © 2013 Johns Manville. 717 17th Street Denver CO, 80202
BID-0157 8/13 (New)