

### PRODUCT DATA SHEET

#### Super Firetemp H

Super Firetemp H is an inorganic, non-combustible, high-temperature insulation for use in industrial equipment and building systems. It can be used on systems operating up to 1700°F (927°C). Composed primarily of lime, silica and reinforcing fibers. This product is white, essentially dust-free, and contains no asbestos, and meets or exceeds ASTM C 656, Type II, Grade 6.

#### THE ADVANTAGES

- Assured Fire Resistance
- Durable
- Economical

#### APPLICATIONS

Since Super Firetemp H has both exceptional strength and insulation qualities, it can be readily machined into component parts of many sizes and shapes. Uses include oven and furnace walls, structural supports, pipe supports, and equipment supports.

#### AVAILABLE FORMS AND SIZES

Thickness . . . . . ½", ¾", 1", 1½", 2" (13, 19, 25, 38, 51 mm)  
 Sheet Size . . . . . 4' x 4' (1.22 m x 1.22 m)  
 . . . . . 4' x 8' (1.22 m x 2.44 m)

Super Firetemp H is available with a sanded finish on one or both sides. The sanded surfaces are smooth and easy to machine.

#### DIMENSION TOLERANCES

Length and Width . . . . . +/- 1/8" (3.2 mm)  
 Thickness . . . . . +/- 1/8" (3.2 mm) Sanded One Side  
 . . . . . +/- 1/16" (1.6 mm) Sanded Two Sides

#### LINEAR SHRINKAGE AFTER 24 HOURS AT TEMPERATURE, %

Temperature					
°F	°C	Length	Width	Thickness	Weight Loss
1200	649	05	0.5	1.0	8
1400	760	1.0	1.0	2.5	10
1600	871	1.0	1.0	2.5	10
1800	982	1.5	1.5	3.5	11

#### THERMAL CONDUCTIVITY

Mean Temperature		"k"	
°F	°C	Btu • in/(hr • ft² • °F)	W/m • °K
200	93	0.61	0.088
400	204	0.66	0.096
600	316	0.73	0.106
800	427	0.80	0.116



#### SPECIFICATION COMPLIANCE

ASTM C656	Type II, Grade 6
ASTM C795 Corrosion: Austenitic Stainless Steel	Passes
ASTM E72	Passes
ASTM E84 Surface Burning Characteristics	Flame Spread -0 Smoke Developed -0
ASTM E119 Building Fire Test	1,2,3,4 Hours
ASTM E136 Non-Combustible	Passes
ASTM E814	Passes
UL 263	1,2,3,4 Hours
UL 1479	3 Hours
UL 1709	1,2,3,4 Hours
NFPA 251	1,2,3,4 Hours
Density (Avg.)	35 pcf (561 kg/m³)
Maximum Recommended Continuous Service Temp.	1700°F (927°C)
Flexural Strength (Avg.)	800 psi (5516 kPa)
Compressive Strength @10% deformation (Avg.)	1600 psi (11032 kPa)
Moisture Content, Normal % of Dry Weight (Avg.)	4%
Maximum Recommended Continuous Service Temp.	1800°F (982°C)
Moisture Content, Normal % of Dry Weight (Avg.)	4%

## ADDITIONAL INFORMATION AND SDS

Please visit our website at [www.jm.com/industrial](http://www.jm.com/industrial)

**CUSTOMER SERVICE, TECHNICAL & GENERAL  
INFORMATION (800) 866-3234**

## CODE COMPLIANCE

Super Firetemp undergoes stringent tests to comply with some of the toughest fire codes in the U.S.



## ISO 9000 CERTIFICATION

Super Firetemp H is manufactured under an ISO 9001:2000 registered quality system. This registration, along with regular independent third-party auditing for compliance, is your assurance that all our products deliver consistently high quality.

## PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

Industrial Insulation Group, LLC manufactures MinWool-1200® mineral fiber pipe, block and a variety of other insulations; Thermo-12® Gold Calcium Silicate pipe and block insulation; Microporous Blanket Insulation; Super Firetemp® fireproofing board; SprouleWR-1200® Perlite pipe and block insulation; high-temperature adhesives, and insulating finishing cement. The physical and chemical properties presented herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Customer Service Office to assure current information. All Industrial Insulation Group products are sold subject to the Johns Manville Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville Limited Warranty and Limitation of Remedy, email [info.industrial@jm.com](mailto:info.industrial@jm.com).

**CUSTOMER SERVICE  
TECHNICAL & GENERAL INFORMATION  
(800) 866-3234**



**Johns Manville**  
Industrial Insulation Group  
2100 LINE STREET • BRUNSWICK, GA 31520