



Johns Manville

## Delta-Aire™ Filtration Media

G.P. 3/4"

### Applications:

General Purpose Filter Media is for use in customer specific applications.

### Roll Specifications:

Roll Widths (m): maximum - 1.83  
Roll Length (lin. m): Standard 60.96.  
(Check for custom lengths)  
Roll Cores - Chipboard: 50.8mm ID

### Variations:

B2 media is fiberglass backed with 0.5 osy polyester.

B1 media is fiberglass backed with a woven fiberglass mat.

Unbacked is fiberglass blanket only.

### Average Physical Properties<sup>(1) (6)</sup>

PRODUCT	G.P. 3/4" UNBACKED	G.P. 3/4" B1	G.P. 3/4" B2
Media Color	Amber	Amber	Amber
Thickness (mm)	19.0	19.0	19.0
Composite Weight (g/m <sup>2</sup> )	229.3	308.9	246.5
Pressure Drop (Pa) <sup>(2)</sup>	20.9	20.9	20.9
Initial Flat Sheet Particle Efficiency(%) <sup>(3)</sup>	20	20	20
Average Atmospheric Efficiency (%) <sup>(4)</sup>	N/A	N/A	N/A
Flammability (UL-Classification) <sup>(5)</sup>	1	1	2

### Notes:

- (1) Values shown in chart are typical, nominal physical properties.
- (2) Nominal pressure drop is measured at an air velocity of 25 ft./min. (0.13 m/sec) through a 2 ft x 2 ft (0.61 m x 0.61 m) flat sheet.
- (3) Efficiency is measured at an air velocity of 25 ft./min. (0.13 m/sec) through a 2 ft x 2 ft (0.61 m x 0.61 m) flat sheet in the 0.3 - 0.5 micron particle size range.
- (4) Applicable to finished air cleaning devices. Results are dependent on filter design and construction. Based on the ASHRAE-52.1 test method.
- (5) Filter media, by itself, is not rated by UL. Classifications shown are potential ratings when media is made into a completed air cleaning device designed to meet those classifications in the UL-900 "Standard for Air Filter Units."
- (6) Johns Manville recommends using filtration media products within six months of the production date.

Johns Manville  
717 17th Street  
Denver, CO 80202  
Tel: (800) 654-3103  
Fax: (303) 978-2318  
[www.jm.com/filtration](http://www.jm.com/filtration)