

# JM EPDM/PVC POURABLE SEALER

## **Features and Components**

Use: JM EPDM/PVC Pourable Sealer is used as a penetration

pocket filler.

**Type:** Two-part polyurethane sealant.

Colors: Part A: Black

Part B: Amber







**System Compatibility** This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

•				,	,		,		Ū	
픋	BUR		APP		SBS					
볼	HA	CA	CA	HW	HA	CA	HW	SA	MF	
Ź		Do not use in Multi-Ply systems								

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened FA = Fully Adhered BA = Ballasted

## **Energy and the Environment**

Maximum VOC	Port A 9. D. 0 a //
IVIAXIIIIUIII VUC	Part A & B: 0 g/l

## **Physical Properties**

Property		JM EPDM/PVC Pourable Sealer		
Percent Volatile	Part A	0%		
Percent volatile	Part B	0%		
Specific Gravity	Part A	1.51		
Specific Gravity @ 77°F (25°C)	Part B	1.24		
Vanar Brassura	Part A	< 0.001@ 68°F (20°C)		
Vapor Pressure	Part B	<1x10-5 mm Hg @ 77°F (25°C)		

#### **Precautions**

Johns Manville EPDM/PVC Pourable Sealer is a combustible material and should be shipped and stored away from open flames, heat or sources of ignition. Keep all cans tightly sealed while in storage. It should be used only in well-ventilated areas. It may cause eye, skin and respiratory irritation, and is harmful or fatal if swallowed. Avoid contact with skin. Use impervious clothing and rubber gloves to avoid prolonged or repeated contact with skin. Read the container label and follow all safety instructions.

# **Installation/Application**



Pour

- Apply between temperatures of: 40° to 90° Do Not Thin.
- Refer to the application instructions guidelines for proper utilization of this sealant.

## **Packaging and Coverage**

Container Sizes	Box of three kits: Part A: 0.75 gal (2.84 I) can Part B: 0.5 pint (0.24 I ) can		
Weight per Can	Part A: 8.7 lb (3.95 kg) Part B: 0.57 lb (0.26 kg)		
Shipping Weight (approx.)	32 lb (14.5 kg)/box		
Boxes per Pallet	45		
Pallet Weight (approx.)	1,500 lb (681.8 kg)		
Pallets per Truck	8 (depends on order size)		

#### **Storage**

Shelf Life	12 months from manufacture date
Storage Conditions	Clean, dry, indoor environment in an unopened container
Temperature Range	$60^{\circ}\text{F} - 75^{\circ}\text{F} (16^{\circ}\text{C} - 24^{\circ}\text{C})$ - Protect from freezing

## **Exposure Window**

Workable pot life after mixing is approximately 30 minutes at 72°F (22°C). The material begins to cure firmly 2 hours after mixing.