

JM EPDM R 60 MIL - FIT

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Features and Components

Membrane: Cured EPDM (ethylene propylene diene monomer) reinforced with a tough 1,000+ denier polyester mat. Excellent puncture and hail resistance.

Factory Inseam Tape: For superior quality assurance and labor savings compared to field fabricated seams.

Fully Extruded: Produces fewer air voids, more uniform thickness and smoother sheets.

Vulcanization Process: Combines two layers of membrane to produce a fully cross-linked monolithic membrane.

Polymer Formulation: Performs in extreme temperature climates and withstands differential movement (elongation).

UV-Stabilization Properties: Offers outstanding ozone and weather resistance delivering one of the longest service lives available.

Technical Expertise: Backed by 30+ years of EPDM experience and installations.



Component

Membrane

Single Ply

Color

Black

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

| 듣 | BUR | APP | | SBS | | | | |
|---|-----------------------------------|-----|----|-----|----|----|----|----|
| 를 | HA | CA | HW | HA | CA | HW | SA | MF |
| Ź | Do not use with Multi-Ply systems | | | | | | | |

| 줕 | TP0 | | | PVC | | | EPDM | | | |
|---|-----|----|----|-----|----|------|------|----|----|----|
| ge | MF | AD | SA | IW | MF | AD | IW | MF | AD | BA |
| Compatible with the selected Single Ply systems a | | | | | | bove | | | | |

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened IW = Induction Weld BA = Ballasted AD = Adhered

Energy and the Environment

| Property | Value | | |
|--------------------------------|-------|--|--|
| Reflectivity* (ASTM C 1549) | 0.06 | | |
| Emissivity* (ASTM C 1371) | 0.87 | | |
| Post-consumer Recycled Content | 0% | | |
| Pre-Consumer Recycled Content | 0% | | |

^{*}Test methods for reflectivity and emissivity are LEED®- and CRRC®-approved.

Peak Advantage® Guarantee Information

Enhanced guarantees are now available on certain systems for wind and puncture.

Consult your local sales representative for more information and for specific guarantee terms and costs.

| Product | Guarantee Term |
|------------------------------------|----------------|
| When used in most JM EPDM Systems* | Up to 20 years |

^{*}Contact JM Technical Services for specific systems.

Codes and Approvals





Installation/Application





Refer to JM EPDM Application Guides and Detail Drawings for instructions.

Packaging and Dimensions

| Roll Size (One-Sided Pre-Tape) | Roll Coverage | Factory Inseam Tape Width | |
|---------------------------------|---|---------------------------|--|
| 10' x 100' (3.05 m x 30.48 m) | 1000 ft ² (92.9 m ²) | 4" (102 mm) | |
| Roll Size (Two-Sided Pre-Taped) | Roll Coverage | Factory Inseam Tape Width | |
| 10' x 100' (3.05 m x 30.48 m) | 1000 ft ² (92.9 m ²) | 4" (102 mm) & 6" (152 mm) | |
| Membrane extruded in: | Milan, OH | | |

Storage

| Shelf Life | 12 months from manufacture date | | |
|--------------------|--|--|--|
| Storage Conditions | The Inseam tape at the end of each roll is susceptible to damage. Store away from areas or materials where punctures or physical damage is likely to occur. Store indoors, out of direct sunlight, keep clean and dry prior to use. Do not stack rolls on top of one another for extended periods of time. | | |
| Temperature Range | 60°F – 80°F (15.6°C – 26.7°C) | | |



JM EPDM R 60 MIL - FIT

Polyester-Reinforced Ethylene Propylene Diene Monomer Membrane

Meets the requirements of ASTM D 4637, Type II

Tested Physical Properties

| Physic | al Properties | ASTM Test Method | Standard for ASTM D 4637, Type II | JM EPDM R 60 mil - FIT System | |
|---------------------------|---|------------------------|--------------------------------------|----------------------------------|--|
| | Breaking Strength (lbf) | D 751 A | >= 90 | 251 | |
| | Elongation at Fabric Break, Ultimate (%) | D 751 A | >= 15 | MD 37, XMD 37* | |
| Strength | Elongation, Ultimate (%) | D 412 | > = 250 | 452 | |
| Stre | Tear Strength (lbf) | D 751 B | >= 10 | 110 | |
| | Dynamic Puncture Resistance, 10J, Type II | D 5635 | pass | pass | |
| | Static Puncture Resistance, 55.1 lbf, Type II | D 5602 | pass | pass | |
| | Overall Sheet Thickness (in.) | D 751 | +/- 10% | pass | |
| <u>.</u> <u>₹</u> . | Thickness Over Scrim, Weathering Side (in.) | D 7635 | 0.015 | 0.026 | |
| Longevity | Brittleness Point (°F) | D 2137 | <=-49 | pass | |
| □ | Ozone Resistance | D 1149 | pass | pass | |
| | Water Absorption (mass %) | D 471 | <=8 | 0.3 | |
| _ e | Heat Aged 670 hrs @ 240°F | D 573 | | | |
| Heat Aged Performance | Breaking Strength (lbf) | D 751 | >= 80 | 232 | |
| leat . | Elongation, Ultimate (%) | D 412 | >= 200 | 270 | |
| | Linear Dimensional Change (%) | D 1204 | <±1 | 0.06 | |
| Weathering Performance | Weathering Resistance, 5040 KJ/(m2-nm) @ 340 nm | D 4637 / G 151 / G 155 | | | |
| Weatl | Visual Inspection | - | pass | pass | |

Physical Properties – Factory Inseam Tape

| Physical Property | JM EPDM R 60 mil - FIT System | | |
|-------------------|-------------------------------|--|--|
| Base | Rubber/Butyl polymer | | |
| Color | Black | | |
| Solvents | None | | |
| Percent Solids | 100% | | |
| Cure State | Partially Cured | | |
| Thickness | 25 mils ± 5 mils | | |
| Width | 4" (102 mm) & 6" (152 mm) | | |
| Release Liner | Polyester | | |