

## Features and Components

JM PMMA Scrim is used in JM PMMA liquid-applied, reinforced membrane systems to improve tear strength, puncture resistance, and crack bridging capabilities. It is a non-woven, chopped strand fabric reinforcement.

**Color:** White



**Component**

**L**  
Liquid

**Type**

**SC**  
Scrim

**M**  
Membrane

**FL**  
Flashing

Liquid Applied  
Multi-Ply

**System Compatibility** This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	CA	HW	HA	CA	HW	SA	MF
<i>Compatible with the selected Multi-Ply systems above</i>									

Single Ply	TPO			PVC		EPDM		
	MF	AD	SA	MF	AD	MF	AD	BA
<i>Do not use in Single Ply systems</i>								

**Key:** HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened AD = Adhered BA = Ballasted

## Peak Advantage® Guarantee Information

Systems	Guarantee Term
Any SBS and BUR roofing system. JM PMMA Membrane system.	Up to 20 years*

\*Contact JM Technical Services for specific system requirements or guarantee terms.

## Codes and Approvals



## Tested Physical Properties

Physical Properties		JM PMMA Scrim	
Strength	Tensile Strength	≥130 long.	≥150 transv.
	Elongation, %	≥50 long.	≥70 transv.
	Tear Resistance	20>daN	
	Puncture Strength	24>daN	
Longevity	Nominal Thickness	30 - 40 mils	
	Water Absorption, %	<1.0	
	Weight, g/m <sup>2</sup>	110	

## Installation/Application

- Please refer to JM PMMA application instructions.

## Packaging and Coverage

Scrim Widths	41.3 in (105 cm)	13.8 in (35 cm)
Scrim Length	164 ft (50 m)	164 ft (50 m)
Scrim Coverage ( <i>net</i> )	536 ft <sup>2</sup> (49.8 m <sup>2</sup> )	160 ft <sup>2</sup> (14.9 m <sup>2</sup> )

## Storage

Shelf Life	Indefinite with proper storage
Storage Conditions	Clean, dry, indoor environment