

Features and Components

Use: For use with JM PMMA membrane systems. JM PMMA Top Coat is combined with JM PMMA Color Pack and JM PMMA Catalyst to form a UV stabilized, resilient finish top coat. The top coat may be smooth or applied with broadcast aggregate.

Type: Elastomeric, liquid-applied top coat.

Color: Not pigmented, Determined by JM PMMA Color Pack

Features: May be combined with JM PMMA Thixo for use on vertical flashings.



Component

L
Liquid

Type

CO
Coating
Multi-Ply

System Compatibility This product may be used as a component in the following systems. Please reference product application for specific installation methods and information.

Multi-Ply	BUR		APP		SBS				
	HA	CA	HW	HA	CA	HW	SA	MF	
	Compatible with all SBS and BUR systems								

Single Ply	TPO				PVC			EPDM		
	MF	AD	SA	IW	MF	AD	IW	MF	AD	BA
	Do not use in Single Ply systems									

Key: HA = Hot Applied CA = Cold Applied HW = Heat Weldable SA = Self Adhered MF = Mechanically Fastened AD = Adhered BA = Ballasted IW = Induction Welded

Energy and the Environment

Maximum VOC (as applied)	1.4 g/l
This product may be used in jurisdictions limiting VOC (volatile organic compounds) content of single ply roofing adhesive to no greater than 250 g/l.	

Peak Advantage® Guarantee Information

Systems	Guarantee Term
Any SBS or BUR roofing system. JM PMMA Membrane system.	Up to 20 years*

*Contact JM Technical Services for specific system requirements or guarantee terms.

Installation/Application



- Apply between 32° and 95° F (0° and 35° C)
- Please refer to the Mixing and Catalyzing instructions on the back side of this data sheet.
- Please refer to JM PMMA application instructions.

Packaging and Coverage

Container Sizes	8.5 kg pail
Pails per Pallet	60 pails
Shipping Weight	Approx 20.8 lbs
Coverage Rate*	355 ft ² /33 m ²

*Coverage, open and dry time rates can vary dramatically depending on the particular substrate and environmental conditions. Coverage rates stated herein are approximate only.

Storage

Shelf Life	12 months from manufacture date
Storage Conditions	Clean, dry, indoor environment in an unopened container
Temperature Range	32°F – 77°F (0°C – 25°C) - Protect from freezing

Mixing and Catalyzing

Thoroughly mix the entire drum of resin for 2-3 minutes before each use, and prior to pouring off resin into a second container if batch mixing. Catalyze only the amount of material that can be used within 10-15 minutes. Add pre-measured catalyst to the resin component, stir for 2-minutes using a slow-speed mechanical agitator or stirring stick, and apply to substrate. The amount of catalyst added is based on the weight of the resin used.

Catalyst per 8.5 kg Unit			
Ambient Temperature	32°F - 50°F (0°C - 10°C)	50°F - 68°F (10°C - 20°C)	68°F - 95°F (20°C - 35°C)
Catalyst	6 (0.6 kg) packets	4 (0.4 kg) packets	2 (0.2 kg) packets
Ambient Temperature Range	32° - 95°F (0° - 35°C)		
Surface Temperature Range	32° - 122°F (0° - 50°C)		
Top Coat Temperature Range	37° - 86°F (3° - 30°C)		
Pot Life*	15 minutes		
Rainproof*	30 minutes		
Next Coat*	60 minutes		
Fully Cured*	3 hours		

*All times listed for 68F (20C) consult data sheet for more information

Clean-Up and Disposal

Clean-Up Information

When work is interrupted or completed, tools must be thoroughly cleaned before the resin hardens.

Disposal Information

For disposal instructions, please refer to the safety data sheet.

Precautions

Handling Refer to product Safety Data Sheet (SDS) for additional information pertaining to this product and prior to use or handling. Roofing contractors must advise their crews to precisely follow all safety, storage, handling, preparation and application instructions. JM will not accept responsibility for any use of this product that does not comply with the instructions printed on the containers.