

Three-Ply Cold Process Modified Bitumen Mineral-Surfaced Roofing System. For use over approved lightweight, insulating fill decks on inclines up to 3" per ft (250 mm/m).

Materials per 100 ft² (9.29 m²) of roof area

Felts:

| | |
|--|---------|
| Base: Ventsulation Felt, GlasBase Plus, DynaBase or PermaPly 28 | 1 layer |
| Intermediate: DynaBase, DynaPly T1, GlasBase Plus, PermaPly 28 or DynaLastic 180 S | 1 layer |

Cap: ♦

| | |
|--|---------|
| 3CLD-CA—DynaKap T1 or DynaKap FR T1 | |
| 3FLD-CA—DynaGlas, DynaGlas FR or DynaGlas 30 FR* | |
| 3PLD-CA—DynaLastic 180, DynaLastic 180 FR, DynaLastic 250 or DynaLastic 250 FR | 1 layer |

* DynaGlas 30 FR must be used in conjunction with DynaBase, DynaPly or DynaLastic 180 S only.

Approximate installed weight: 165 - 360 lb (75 - 163 kg).

General

This specification is for use over any type of approved, lightweight, insulating fill deck (without insulation) which can receive and adequately retain mechanical fasteners that may be recommended by the deck manufacturer. Examples of these decks are lightweight, insulating concrete, either cellular-type or aggregate-type. Ventsulation venting base felt is recommended over any wet fill deck, and may be required as a condition of guarantee. JM also recommends the use of FP-10 One-Way Roof Vents over some types of wet fill decks.

Design and installation of the deck and/or roof substrate must result in the roof draining freely, to outlets numerous enough and so located as to remove water promptly and completely. Areas where water ponds for more than 24 hours are unacceptable and will not be eligible for a JM Peak Advantage Guarantee.

Flashings

Flashing details can be found in Section 3 of the JM Commercial/Industrial Roofing Systems Manual.


Application

On roof decks with slopes up to ½" per ft (41 mm/m), the roofing felts and modified bitumen sheets may be installed either perpendicular or parallel to the roof incline.

Using one of the base felts listed, start with a piece 24" (610 mm) wide. The remaining felts are to be applied full width with 3" (76 mm) side and 4" (102 mm) end laps over the preceding sheets. Nail the laps at 9" (229 mm) centers, and down the longitudinal center of each felt place two rows of nails, with the rows spaced approximately 11" (279 mm) apart, and nails staggered on approximately 18" (457 mm) centers. Use nails or fasteners appropriate to the type of deck, with 1" (25 mm) minimum diameter caps. Consult the current FM ApprovalsSM RoofNav for the appropriate base sheet, fastener type and pattern. For additional fastener information, refer to the "Roof Decks" section of the current JM Commercial/Industrial Roofing Systems Manual.

Roll a 19¾" (502 mm) wide piece of one of the intermediate felts listed into a full coating of MBR Cold Application Adhesive or MBR Bonding Adhesive. The remaining felts are to be applied full width, in the same manner. End and side laps can be done in one of the following ways:

- Use MBR Cold Application Adhesive or MBR Bonding Adhesive on the 3" (76 mm) side and 6" (152 mm) end lap. **Or...**
- Use a hot air gun or torch on the 3" (76 mm) side and 6" (152 mm) end lap. All laps must be rolled with a 3" (76 mm) rounded edge roller.



A ⅛" to ⅜" (3 mm to 10 mm) bleedout of SBS compound shall be visible at the edge of all seams. All laps must be checked for good adhesion.

Cap sheet application is accomplished in one of the following ways:

- Apply a full width piece of one of the cap sheets listed into a full coating of MBR Cold Application Adhesive or MBR Bonding Adhesive. Subsequent sheets are to be applied in the same manner, with 4" (102 mm) side and 6" (152 mm) end laps over the preceding sheets.

Or...

- Prepare the 6" (152 mm) end lap by removing all loose granules. Heat and embed all remaining granules with a hot air gun or torch. Apply heat to the 3" (76 mm) side and 6" (152 mm) end lap making sure both have a good compound flow to adhere the two surfaces. All laps must be rolled with a 3" (76 mm) rounded edge roller. A ⅛" to ⅜" (3 mm to 10 mm) bleedout of SBS compound shall be visible at the edge of all seams. All laps must be checked for good adhesion.

Subsequent sheets are to be applied in the same manner.

Application of JM SBS modified bitumen products may require the use of a hot air gun or torch. Improper use of these materials and application equipment can result in severe burns, and/or other physical injury, as well as damage to property. In order to prevent these situations the mechanic must install the materials using the techniques recommended by JM and those found in "A Guide to Safety: Torch-On Modified Bitumens" available from the Asphalt Roofing Manufacturers Association. These techniques have been endorsed by the National Roofing Contractors Association and the United Union of Roofers, Waterproofers and Allied Workers.

Note: When using metric- and English-sized base and cap sheets in the same system, care must be taken to avoid lap over lap configurations.

For cold weather application techniques, refer to Paragraph 24.0 of Section 3d.

Steep Slope Requirements

Special procedures are required on inclines over ½" per ft (41 mm/m). Refer to Paragraph 21.0 of Section 3d.

Surfacing

No additional surfacing is required.

Note: For the most current information on general guidelines, please refer to the System Considerations tab under Systems Introduction & Selection on the JM Roofing Web site. For specifications, flashing details and general installation information please refer to the System Application tab.

Refer to the Material Safety Data Sheet and product label prior to using this product.