

## Two-Ply Hot Mopped Modified Bitumen Mineral-Surfaced Roofing System. For use over plywood or other nailable decks on inclines up to 3" per ft (250 mm/m).

### Materials per 100 ft<sup>2</sup> (9.29 m<sup>2</sup>) of roof area

**Sheathing Paper:** Wood board decks only 1 layer

#### Base Felts:

GlasBase Plus, DynaPly T1, DynaBase or PermaPly 28 1 layer

**Note:** DynaBase and DynaPly – Full Sheet width is 39½" (1 m) GlasBase Plus and PermaPly 28 – Full Sheet width is 36" (0.92 m)

#### Cap: ♦

2CND—DynaKap T1 or DynaKap FR T1

2FND—DynaGlas or DynaGlas FR

2PND—DynaLastic 180, DynaLastic 180 FR, DynaLastic 250 or DynaLastic 250 FR 1 layer

**Asphalt:** Trumbull®\* or other JM-approved asphalt

Incline per foot	Asphalt	Total Weight
Up to ½" (41 mm/m)	190°F (88°C), Type III, Steep	46 lb (21 kg)
½" to 3" (41 to 250 mm/m)	220°F (104°C), Type IV, Special Steep	46 lb (21 kg)

Approximate installed weight: 140 - 240 lb (64 - 109 kg)

### General

This specification is for use over any type of approved structural deck (without insulation) which can receive and adequately retain nails or other mechanical fasteners that may be recommended by the deck manufacturer. Examples of these decks are wood, plywood and approved oriented strand board (OSB). This specification is not for use directly over light-weight, insulating concrete decks.

**Design and installation of the deck and/or roof substrate must result in the roof draining freely, to outlets numerous enough and so located as to remove water promptly and completely. Areas where water ponds for more than 24 hours are unacceptable and will not be eligible for a JM Peak Advantage Guarantee.**

**Note:** All general instructions contained in the current JM Commercial/Industrial Roofing Systems Manual shall be considered part of this specification.

### Flashings


Flashing details can be found in Section 3 of the JM Commercial/Industrial Roofing Systems Manual.

### Application

On roof decks with slopes up to ½" per ft (41 mm/m), the roofing felts and modified bitumen sheets may be installed either perpendicular or parallel to the roof incline.

Over wood board decks, one ply of sheathing paper must be used under the base felt, next to the deck.

Using one of the base felts listed, start with a piece ½ sheet wide. The remaining felts are to be applied full width with 3" (76 mm) side and 4" (102 mm) end laps over the preceding sheets. Nail the laps at 9" (229 mm) centers, and down the longitudinal center of each felt place two rows of nails, with the rows spaced approximately 11" (279 mm) apart, and nails staggered on approximately 18" (457 mm) centers. Use nails or fasteners appropriate to the type of deck, with 1" (25 mm) minimum diameter caps. For additional fastener information, refer to the "Roof Decks" section of the current JM Commercial/Industrial Roofing Systems Manual.



Apply a full width piece of one of the cap sheets listed into a full mopping of asphalt. Subsequent sheets are to be applied in the same manner, with 4" (102 mm) side and end laps over the preceding sheets, with 6" [152 mm] end laps for DynaLastic products).

Apply all felts so that they are firmly and uniformly set, without voids, into the hot asphalt. Asphalt temperature should be at the Equiviscous Temperature (EVT), ±25°F (±14°C), at the point of application. All felt edges shall be well sealed. The asphalt shall be applied just before the felt, at a nominal rate of 23 lb/100 ft<sup>2</sup> (11 kg/9.29 m<sup>2</sup>). For modified bitumen sheets, the asphalt temperature shall be at a minimum of 400°F (204°C) when the sheet is set into it. This higher temperature maximizes the bonding of the modified bitumen sheet.

**Note:** When using metric- and English-sized base and cap sheets in the same system, care must be taken to avoid lap-over-lap configurations.

**Base sheets and cap sheets with polyester reinforcement must be allowed to relax in an unrolled position prior to installation.**

For cold weather application techniques, refer to Paragraph 24.0 of Section 3d.

### Steep Slope Requirements

Special procedures are required on inclines over ½" per foot (41 mm/m). Refer to Paragraph 21.0 of Section 3d.

### Surfacing

No additional surfacing is required.

### Asphalt

Asphalt should meet the requirements of ASTM D 312.

JM guarantees require the use of Trumbull®\* asphalt or another JM-approved asphalt.

**Note:** For the most current information on general guidelines, please refer to the System Considerations tab under Systems Introduction & Selection on the JM Roofing Web site. For specifications, flashing details and general installation information please refer to the System Application tab.

\* Trumbull is a registered trademark of Owens Corning.

Refer to the Material Safety Data Sheet and product label prior to using this product.