# MultiStar® 566

### **Product description:**

MultiStar® 566 is an assembled roving manufactured with continuous glass fibers of defined diameter into a cylindrical roving package with a sizing suitable for chopping and designed for excellent performance in composites panel production.

Composite materials made with MultiStar® 566 roving have very good fiber distribution and resin translucency for panel systems.

MultiStar® 566 used in translucent panels are used in commercial, industrial and public buildings. They can also find applications in the public segment, such as car and bicycle parks where comfortable translucent roofs brings lighting comfort to endusers.

#### **Benefits:**

- Good unwinding and chopping
- Good processing for panel fabrication
- Flat and homogenous mat forming
- Fast impregnation
- Excellent translucency
- · Qualified in weaving processes
- ISO 14001 certified production

## **Resin compatibility:**

- Unsaturated polyester
- Epoxy



## **Designation:** Glass type is E-Glass

JM Designation	Region	Roving bundle linear density (tex)	Sizing content (%)	Moisture content Max.(%)	Strand linear density Tex (g/km)	Stiffness minimum (mm)
MultiStar® 566 2400 35	EU	2400	0.65	0.15	35	80

#### **Bobbin dimensions:**


Region	JM Designation	Typical weight (kg)	Inner diameter (mm)	Outer diameter (mm)	Height (mm)	Bobbin wrap
EU	All MultiStar® 566 Types	20	77	280	270	PE Bag

### Packaging:

Region	JM Designation	Packaging type	Pallet dimensions (mm)	Net weight per pallet (kg)	Bobbins per pallet
EU	All MultiStar® 566 Types	Cardboard box	1200 x 880	960	48
			1180 x 1180	1280	64

### **Storage:**

These products should be stored in original packaging in dry, roofed, dust free storehouses. The recommended temperature is between  $10^{\circ}\text{C}$  to  $30^{\circ}\text{C}$  ( $50^{\circ}\text{F}$  to  $86^{\circ}\text{F}$ ) at relative air humidity between 50% to 75%. The products should remain in the original packaging and be conditioned in the work area for a minimum of 24 hours prior to use. The pallets should be single stacked unless otherwise specified on the packaging unit.



Technical specifications as shown in this literature are intended to be used as general

guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of this product represent typical, average values obtained in accordance with accepted test methods and are subject to normal

manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the Regional Sales Office nearest you for the most

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on Johns Manville products, please visit <a href="https://www.jm.com/en/login/policies-terms-and-conditions/">https://www.jm.com/en/login/policies-terms-and-conditions/</a>

### Values:

All data represent typical average values.

## JM Johns Manville

#### **US Headquarters**

Johns Manville 717 17th Street Denver, CO 80202 - USA Phone: +1 (303) 978 2000

#### <u>Customer-Service-Offices:</u> North America

Johns Manville 7500 Dutch Road Waterville, OH 43566 - USA Phone: +1 (800) 554 4826 Fax: +1 (419) 878 1538

#### Europe

Warranty disclaimer:

current information.

or call (800)654-3103.

Johns Manville Slovakia, a.s. Strojárenská 1 91799 Trnava - Slovakia Phone: +421 (0) 33 5918 249

Phone: +421 (0) 33 5918 249 Contact: fibers@jm.com www.jm.com