

# StarRov® 886

## Product description:

StarRov® 886 direct roving is manufactured by direct winding of continuous glass fibers of defined diameter into a cylindrical roving package.

It is characterized by a pioneering reactive sizing designed for Structural Thermoplastic Composites with polyamide engineering polymers.

The JM proprietary sizing chemistry renders the glass surface reactive and enables in-situ polymerization from glass. It maximizes glass-matrix bonding which leads to improved strength, impact, aged and dimensional stability performance.

Rovings with Reactive (RXN) 886 sizing are designed to be used mainly as an input for TP-RTM, TP-RIM, TP-pultrusion, and TP-filament winding processes with polyamide resins. The majority of the applications targeted are in the automotive market where strength to weight ratio is important.

## Resin compatibility:

- Polyamide resins

**Designation:** Glass type is E-Glass

## Benefits:

- Enables in-situ polymerization with higher strength performance.
- Maximizes glass-matrix bonding.
- Improving strength (ILSS).
- Improved impact properties.
- Suitable for a variety of processes, including TP-RTM, TP-RIM, TP-pultrusion, and TP-filament winding.
- Possible one-pot system simplified processing – no issues with curing in mixing head or tubing.
- Low cost thermoplastic with the potential of greatly improved property profile.
- End of life recyclability.
- European products are manufactured in compliance with ISO 9001 standards.



SEM picture indicating excellent matrix-glass bonding in PA6 system

JM Designation	Region	Filament diameter (µm)	LOI content (%)	Linear density Tex (g/km)
StarRov® PR 220 1200 886	EU	16	0.55	1200
StarRov® PR 440 2400 886	EU	16	0.55	2400

**Bobbin dimensions:**

Region	Typical weight (kg)	Inner diameter (mm)	Outer diameter (mm)	Height (mm)
EU	19 - 20	165	300 - 310	260 - 290

**Packaging:**

Region	Packaging wrap	Pallet dimensions (mm)	Net weight per pallet (kg)	Bobbins per pallet
EU	Stretch foil	1285 x 960 x 1400	920	48

**Storage:**

These products should be stored in original packaging in dry, roofed, dust free storehouses. The recommended temperature is between 10°C to 30°C (50°F to 86°F). The products should remain in the original packaging and be conditioned in the work area for a minimum of 24 hours prior to use. The pallets should be single stacked unless otherwise specified on the packaging unit.

**Warranty disclaimer :**

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of this product represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the Regional Sales Office nearest you for the most current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on Johns Manville products, please visit <https://www.jm.com/en/login/policies-terms-and-conditions/> or call (800)654-3103.

**Values:**

All data represent typical average values.

**US Headquarters**

Johns Manville  
717 17th Street  
Denver, CO 80202 - USA  
Phone: +1 (303) 978 2000

**Customer-Service-Offices:****North America**

Johns Manville  
7500 Dutch Road  
Waterville, OH 43566 - USA  
Phone: +1 (800) 554 4826

**Europe**

Johns Manville Slovakia, a.s.  
Strojársená 1  
91799 Trnava - Slovakia  
Phone: +421 (0) 33 5918 249  
Contact: [fibers@jm.com](mailto:fibers@jm.com)

**[www.jm.com](http://www.jm.com)**