

SINGLE-END ROVING

Product Characteristics			Region		Resin / Polymer Type	Tex (g/km)	300	410	600	1100	1200	2000	2200	2400	4400	4800	9600	FDA - NA	Food Contact EU (>2016)	
Tradename	Process	Sizing	NA	EU		Yield (yds/lb)	1655	1210	828	450	414	250	225	207	113	103	56			
						Ø (µm)	13	13	14	16	16	22	16	16	23	23	32			
StarRov®	LFT + D-LFT	490		•	PP					•				•				•	•	
		485	•		PP				•				•						•	
		853	•	•	PPS/PPA/PBT									•	•					
		895	•	•	PA					•				•	•					
	Organo Sheets/ TP-RTM	490			•	PP					•						•			•
		895	•	•	PA						•			•	•					
		853	•	•	PPS/PPA/PBT										•	•				
		886 RXN			•	PA					•				•					
	Pultrusion	090	•	•	UP/VE/Epoxy/PU					•		•	•	•	•	•	•	••		
		086			•	UP/VE/Epoxy	•	•	•		•			•			•			
		507	•			Phenolic										•				
	Weaving / NCF / MAX	086			•	UP/VE/Epoxy	•	•	•		•			•			•			
		090	•	•	UP/VE/Epoxy					•		•	•	•	•	•	•	••		
	Filament Winding	086			•	UP/VE/Epoxy	•	•	•		•			•			•			
090		•	•	UP/VE/Epoxy/PU					•		•	•	•	•	•	•	••			

The Food Contact compliance for Europe (> 2016) is based on the requirements of the Commission Regulation (EU) 10/2011 on plastic materials and articles intended to come into contact with food.

The table provides only a guideline within JM product range. For specific questions, please ask a JM representative or send mail to fibers@jm.com.