

DESCRIPTION

Microlite® White PSK Formaldehyde-free™ duct wrap insulation is a lightweight, highly resilient, blanket-type thermal insulation. The insulation blanket is manufactured from rotary-process fiberglass bonded with a Formaldehyde-free™ resin.

AVAILABLE FORMS

Microlite White PSK Formaldehyde-free™ insulation is available in a variety of densities, thicknesses and roll lengths. It is supplied with a White PSK (polypropylene-scrim-kraft) vapor barrier facing to meet installed performance requirements, with a 2" (51 mm) stapling tab. Microlite PSK White comes 48" (1219 mm) wide.

USES

Microlite White PSK insulation is recommended as thermal insulation for the exterior of HVAC systems or other spaces or surfaces where temperature control is required. Great aesthetics and superior cleanability make White PSK an ideal choice for specifications.

STORAGE

Microlite White PSK Duct Wrap should be kept clean and dry during storage, transport, installation, and system operation.

FACING INFORMATION

White PSK Metalized Polypropylene
Reinforced with fiberglass scrim laminated to UL-rated kraft.
Permeance: 0.02 perms*

**Per ASTM E96, Procedure A for facing material prior to lamination. After lamination, permeance values may be higher.*

GENERAL PROPERTIES

| | |
|------------------------------------|---------------------------|
| Temperature (max.) – ASTM C411 | 250°F (121°C) |
| Water vapor sorption – ASTM C1104 | <5% by weight |
| Corrosivity with steel – ASTM C665 | Does not accelerate |
| Fungi resistance – ASTM C1338 | Does not breed or promote |

THICKNESSES AND PACKAGING

| Type | 100' Roll | 75' Roll | 50' Roll |
|------|--------------------|----------|----------|
| | (31 m) | (23 m) | (15 m) |
| | Thickness, in (mm) | | |
| 75 | 1½ (38) | 2 ½ (56) | 3 (76) |
| 100 | – | 2 (51) | – |

Note: Additional thicknesses, widths and other lengths available on special order. Contact Regional Sales Office for availability.

RECYCLED CONTENT



SURFACE BURNING CHARACTERISTICS

Microlite insulation meets the Surface Burning Characteristics and Limited Combustibility of the following standards:

Standard/Test Method

- ASTM E84
- UL 723
- NFPA 90A and 90B
- UL Guide No. 40 U8.3. Card R3711
- CAN/ULC S102

| | |
|-------------------------------|----|
| Maximum Flame Spread Index | 25 |
| Maximum Smoke Developed Index | 50 |

Note: Faced materials are tested as composite products (insulation, adhesive and facing).

SPECIFICATION COMPLIANCE

ASTM C1290* Type 75 & 100

**Facing provided free of print for aesthetic purposes.*

ASTM C553**

Type I, Type II Type 75 & 100

***For faced material: 250°F (121°C) maximum temperature.*

ASTM C1136s†

Type II PSK Facing

†Replaces HH-B-100B, Type II.

Canada: CGSB 51-GP-11M

SUSTAINABLE BUILDING CERTIFICATIONS

| | |
|-------------------|-----------|
| GREENGUARD® | Certified |
| GREENGUARD® GOLD | Certified |
| FORMALDEHYDE FREE | Validated |

GREENGUARD® Certified products have been screened for more than 10,000 volatile organic compounds (VOCs) and meet stringent standards for low chemical emissions based on established criteria from key public health agencies. This product is also a UL Validated Formaldehyde-Free product, meeting recommendations established by the California Air Resources Board and the EPA to use building materials and insulation made without formaldehyde.



MICROLITE® WHITE PSK

WHITE PSK-FACED FORMALDEHYDE-FREE™ FIBERGLASS DUCT WRAP

DATA SHEET

APPLICATION RECOMMENDATIONS


The R-value will vary depending upon how much the insulation is compressed during installation. To obtain the published installed R-values, the insulation stretch-out should be determined using the following table:

DUCT WRAP STRETCH-OUTS

| Labeled Thick. (in) | Installed Compressed Thickness (in) | Stretch-out Dimension | | |
|---------------------|-------------------------------------|-----------------------|----------|-------------|
| | | Round | Square | Rectangular |
| 1½ | 1.125 | P+ 9.5" | P+ 8.0" | P+ 7.0" |
| 2 ½ | 1.65 | P+ 13.0" | P+ 11.0" | P+ 8.5" |
| 3 | 2.25 | P+ 17.0" | P+ 14.5" | P+ 11.5" |
| 2 ½ | 1.65 | P+ 13.0" | P+ 11.0" | P+ 8.5" |
| 3 | 2.25 | P+ 17.0" | P+ 14.5" | P+ 11.5" |

Stretch-outs include 2" (51 mm) for overlap. P = perimeter of duct to be insulated.

Prepare overlap by removing approximately 2" (51 mm) of insulation from facing.



THERMAL CONDUCTIVITY (ASTM C518)

| Type | k* | | k | |
|------|----------------------|----------------------|--------------------|-------------------|
| | Compressed Thickness | Compressed Thickness | Labeled Thickness | Labeled Thickness |
| | Btu•in/(hr•ft²•°F) | W/m•°C | Btu•in/(hr•ft²•°F) | W/m•°C |
| 75 | 0.27 | 0.039 | 0.29 | 0.042 |
| 100 | 0.25 | 0.036 | 0.27 | 0.039 |

Conductivity at 75°F (24°C) mean temperature.

*Tested with material thickness compressed 25%.

INSTALLATION

Before applying duct wrap, sheet metal duct shall be clean, dry and tightly sealed at all joints and seams. Wrap insulation around duct with facing to the outside so the 2" (51 mm) flap completely overlaps facing and insulation at the other end of stretch-out. Insulation shall be snugly butted.

Secure seams with outward clinching staples placed approximately 6" (152mm) on center or tape tabs of 8" or longer. If required, seal seam with pressure-sensitive tape designed for use with duct insulation. For best results, Johns Manville recommends the use of (96mm) Johns Manville Microlite White PSK Duct Wrap Seaming Tape. Please refer to HVAC-475 for more information on tape. When adhering the tape, apply pressure by rubbing the tape firmly down with a plastic squeegee. Insulation on the underside of ducts spanning 24" (610 mm) or greater shall be secured with mechanical fasteners and speed clips spaced approximately 18" (457 mm) on center. Fasteners should be cut off flush after the speed clips are installed and sealed with the same tape as specified above.

Adjacent sections of duct wrap insulation shall be snugly butted with the circumferential 2" (51 mm) tape flap overlapping and secured as recommended for the longitudinal seam. When a vapor seal is required, the use of Johns Manville Microlite White PSK Duct Wrap Seaming Tape is preferred.

GUIDE SPECIFICATIONS

Insulation for Metal Ducts. All ducts shall be insulated on the outside with a Formaldehyde-free™, flexible glass fiber blanket. Microlite White PSK-faced Formaldehyde-free™ fiberglass duct wrap insulation should have a minimum installed R-value* of _____, a Type _____ density and a white PSK facing. Tape shall be Johns Manville Microlite White PSK Duct Wrap Seaming Tape. Insulation shall be furnished with a factory-applied facing with a composite UL FHC rating of 25/50.

*The minimum insulation installed R-value should be determined in accordance to the duct operating and ambient conditions.

INSTALLED R-VALUES

| Type | Labeled Thickness | | Installed "R"*** | | Out-of-Package "R" | |
|------|-------------------|----|------------------|---------|--------------------|---------|
| | in | mm | (hr•ft²•°F)/Btu | m²•°C/W | (hr•ft²•°F)/Btu | m²•°C/W |
| 75 | 1½ | 38 | 4.2 | 0.74 | 5.2 | 0.92 |
| | 2 ½ | 56 | 6.0 | 1.08 | 7.5 | 1.33 |
| | 3 | 76 | 8.3 | 1.46 | 10.3 | 1.81 |
| 100 | 2 | 51 | 6.0 | 1.06 | 7.4 | 1.30 |

***Installed R-value calculated with a material thickness compressed to a maximum of 25% following recommended duct wrap stretch-outs.



717 17th St.
Denver, CO 80202
800-654-3103
www.JM.com

North American Sales Offices, Insulation Systems

Eastern Region & Canada
P.O. Box 158
Defiance, OH 43512
800-334-2399
Fax: 419-784-7866

**Western Region & Outside
North America**
P.O. Box 5108
Denver, CO 80217
800-368-4431
Fax: 303-978-4661

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of Microlite White PSK listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit www.jm.com/terms-conditions or call (800) 654-3103.