

# MINWOOL-1200® PRECISION CUT

WATER-REPELLENT, HIGH-TEMPERATURE MINERAL WOOL INSULATION

**DATA SHEET** 

### MINWOOL-1200® PRECISION CUT

MinWool-1200 Precision Cut (PC) Pipe Insulation is a water-repellent mineral wool insulation made of inorganic fibers derived from basalt, a volcanic rock, with thermosetting resin binder. Advanced manufacturing technology ensures consistent product quality, with high fiber density and low shot content, for excellent performance in thermal control and fire resistance applications. PC Pipe insulation is a factory "V" grooved mineral wool board manufactured to specific pipe or vessel sizes with a variety of facing options. It ships flat in 4 mil plastic and allows easy forming at the job site.

## **ADVANTAGES**

**Water-Repellent.** Minwool-1200 Precision Cut insulation is water-repellent to help mitigate the risk of water intrusion. MinWool-1200 Precision Cut performs in accordance with BS EN 1609:2013, absorbing less than 0.35kg/m² of water during water absorption tests at temperatures up to 425°F (218°C).

**Ships Flat.** Packaged flat in 4 mil plastic for some weather protection (see guide spec), freight efficiency and storage space utilization.

**Thermal Performance.** Good thermal conductivity values help maximize control of heat loss, contributing sto reduced operating costs and greater energy savings.

**Light Weight, Low Dust, Protected Outer Surface**. Easy to handle and fabricate, is easy to cut with a knife. Clean handling properties and factory applied facers help reduce skin irritation and minimize job cleanup time and expense.

**Mold Resistant**. PC pipe insulation does not support the growth of fungi.



Operating Temperature Limit: 1200°F (650°C)

## **APPLICATIONS**

PC pipe insulation is produced in 3 foot sections to fit NPS for commercial and industrial applications at temperatures ranging from ambient to 1200°F (650°C). This formed pipe/vessel insulation is easily fabricated, cutting cleanly and easily with a knife. Very low in-service shrinkage helps prevent gaps from forming at joints, preventing costly thermal leaks. The insulation is designed to be factory or field jacketed. It may be installed directly on hot surfaces; system shutdown and staged heat-up are not required.

### **AVAILABLE FORMS AND SIZES**

## **Standard Thicknesses**

Single Layer- 1" thick up to 4" thick Double Layer- Over 4" thick in ½" increments Sizes range from ½" to 44" pipe sizes Available in iron pipe sizes

#### **Facings Available**

Sizes ½" through 2½" is supplied with no facing Sizes 3" and above are supplied with a fiberglass mat facing Other facings available include ASJ

## **Linear Shrinkage After 24 Hours at Temperature**

Temperature		Shrinkage
°F	°C	(%)
1050	566	0
1200	649	<2

### **SPECIFICATION COMPLIANCE**

ASTM C447 Maximum Service Temperature	1200°F (650°C)	
ASTM C547, Material Specification	Type III, Grade A	
ASTM C585 Dimensions of Pipe Insulation	Passes	
ASTM C795/C871/C692 Corrosion: Austenitic Stainless Steel	Passes	
ASTM C1335 Shot Content	<25%	
ASTM C1338 Fungi Resistance	Passes	
ASTM E84 Surface Burning Characteristics	Flame Spread - 25 Smoke Developed - 50 or less	
ASTM E136 / ISO 1182 Non-Combustible	Passes	
Recovery after 10% Compression	100%	
BS EN 13472:2013* Water Absorption	<0.35 kg/m <sup>2</sup>	
	·	


<sup>\*</sup>Tested in accordance with BS EN 13472 by testing via BS EN 1609 on fabricated board

## MINWOOL-1200® PRECISION CUT

WATER-REPELLENT, HIGH-TEMPERATURE MINERAL WOOL INSULATION

**DATA SHEET** 

#### THERMAL CONDUCTIVITY



<sup>\*</sup> MinWool-1200 Precision Cut Pipe Insulation as tested in accordance with ASTM C518.

#### PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

### **QUALITY STATEMENT**

Johns Manville Industrial Insulation products are designed, manufactured and tested to strict quality standards in our own facilities. This along with third party auditing is your assurance that this product delivers consistent high quality.

### **ADDITIONAL INFORMATION AND SDS**

Please visit our website at www.jm.com/industrial Customer Service, Technical & General Information: (800) 866-3234



717 17th St. Denver, CO 80202 (800) 866-3234 JM.com Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of the MinWool-1200 Precision Cut listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit www.jm.com/terms-conditions or call (800) 654-3103.