

GL-30

Product Data Sheet

Value

General Description

GL-30 is a flame retardant vapor barrier facing consisting of 0.00125" white metallized polypropylene film, a combination of fiberglass reinforcing yarn and natural kraft paper laminated together with a flame retardant adhesive. This product is typically used as a facing for metal building insulation.

Construction

Properties

	English	<u>Metric</u>
Polypropylene Film	0.00125 "	32 microns
Fiberglass Reinforcing Yarn	MD:4/ inch	MD:16 / 100mm
	XD: 4/ inch	XD: 16 / 100mm
Adhesive	Flame RetardantFlame Retardant	
Natural Kraft Paper	30 lbs / 3000 ft ² _	49 gm / m²

Test Method

Typical Physical Properties

1 10 0011100	1 cot iviourioa	<u>varao</u>	
		English	Metric
Basis Weight	Scale	25 lbs / MSF	122 gm / m ²
Permeance (MVTR)	ASTM E-96, Procedure A	.02 max	.013 max
Puncture Resistance	ASTM D-781	50 scale Units	58 scale Units
Tensile Strength ASTM D-828	MD: 45 lbs / in	MD: 7.9 kn/m	
-		XD: 30 lbs / in	XD: 5.3 kn/m
Mullen Burst	ASTM D-774	45 psi	3.2kg / cm ²
Mold & Mildew Resistance	ASTM D-2020	None	None
Corrosion	120F (49C) @ 95%RH (30 days)	None	None
Delamination	120F (49C) @ 95%RH (30 days)	None	None
High Temp. Resistance	24 hours @ 150F (66C)	Pass	Pass
Adhesion	1 hour water @ 70F (21C)	Pass	Pass
Flammability	ASTM E-84	Flame Spread <25 Same	
		Smoke <50	Same

U. L. Surface Burning Characteristics Film Exposed Kraft Exposed Flame Spread 0 10 Smoke 10 10

This product meets ASTM C1136-90 requirements for insulation facings.

The physical (or chemical) properties of Johns Manville products represent typical average values obtained in accordance with acceptable test methods and are subject to normal manufacturing variations. Values are supplied as a technical service and are subject to change without notice. Rev. 1-1/18/07

Hamilton Technologies, A Business of Johns Manville Corporation
7400 Ranco Road Corporate Headquarters- 717 17TH Street
Richmond, VA 23228 Denver, CO 80202
(804) 261-7400 / FAX (804) 261-7405 (303) 978-2000