

## CALBOND GOLD

CalBond Gold is a low VOC modified, silicate-based glue for thermal insulations. It sets quickly to provide a high-temperature bond for porous insulating materials. CalBond Gold is asbestos free.

### ADVANTAGES

- Easy to use, sets quickly.
- Excellent adhesion strength to calcium silicate insulation, the glue line joint will outlast the insulation itself.

### APPLICATIONS

CalBond Gold is useful for bonding sections of calcium silicate or perlite high-temperature pipe or block insulation, to make mitered elbows, large insulating sections or other special shapes.

### WET PROPERTIES

Density	12 lbs./gal. (1.44 kgs./liter), avg
Solids by Weight	62% avg
pH	13.5 avg
Wet Coverage	1/16" thick, 25 sq. ft./gallon (1.6 mm, 0.61 m <sup>2</sup> /liter) 1/32" thick, 50 sq. ft./gallon (0.8 mm, 1.23 m <sup>2</sup> /liter)

### DRYING TIME ON CALCIUM SILICATE INSULATION

(ASTM C474-67 AT 77°F [25°C])	
Set	15 seconds
Handle	5 minutes
Thorough Dry	1 ½ hours
Minimum Application Temperature for Thorough Dry	32°F (2°C)

### SPECIFICATION COMPLIANCE

ASTM C447 Max Service Temp.	Passes
ASTM C665 Corrosivity to Steel	Passes
ASTM C795/C871/C692	Passes
ASTM E136 Non Combustible	Passes
Mil-I-24244	Passes
Reg Guide 1.36	Passes
EPA Test for VOC	< 5%

### AVAILABLE SIZE OPTIONS

1, 2, and 5 gallon buckets
55 gallon drums



### PHYSICAL PROPERTIES

Shore "C" Hardness 24 Hour Cure	65 Minimum
Elongation – 10-Day Cure	2%
Shrinkage – 10-Day Cure	1%
Tensile Strength	3000 psi (20,685 kPa)
Adhesion to Calcium Silicate Insulation	Insulation Fails Before Glue Line Joint

### CHEMICAL RESISTANCE

Non-Aqueous Solvents	Excellent with Aromatic, Aliphatic and Oxygenated Solvents
Mineral Acids	Salt Formation and Loss of Bond Strength
Water – Cold	Softens Upon Lengthy Submersion
Water – Hot	Softens Upon Continuous Contact

### STORAGE AND APPLICATION LIMITATIONS

Shelf Life	3 Years from Date of Manufacture
Effect on Metal (Dry Product)	Non-Corrosive
Store between 35°F and 95°F	
Clean Up: Use hot water and soap before drying. Maximum Recommended Continuous Service Temperature (Dry Product) 1000°F (538°C)	

## PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

## QUALITY STATEMENT

Industrial Insulation Group Products are designed, manufactured and tested to strict quality standards in our own facilities. This along with third party auditing is your assurance that this product delivers consistent high quality.

## ADDITIONAL INFORMATION AND SDS

Please visit our website at [www.jm.com/industrial](http://www.jm.com/industrial)  
Customer Service, Technical & General Information: (800) 866-3234



717 17th St.  
Denver, CO 80202  
(800) 866-3234  
JM.com

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of the Calbond® Gold listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you for current information.

**All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit [www.jm.com/terms-conditions](http://www.jm.com/terms-conditions) or call (800) 654-3103.**